UvA-DARE (Digital Academic Repository)

Conformational studies of ligand-template assemblies and the consequences for encapsulation of rhodium complexes and hydroformylation catalysis

Jacobs, I.; van Duin, A.C.T.; Kleij, A.W.; Kuil, M.; Tooke, D.M.; Spek, A.L.; Reek, J.N.H.

DOI

[10.1039/c3cy20665c](https://doi.org/10.1039/c3cy20665c)

Publication date

2013

Document Version

Final published version

Published in

Catalysis Science & Technology

[Link to publication](#)

Citation for published version (APA):

Jacobs, I., van Duin, A. C. T., Kleij, A. W., Kuil, M., Tooke, D. M., Spek, A. L., & Reek, J. N. H. (2013). Conformational studies of ligand-template assemblies and the consequences for encapsulation of rhodium complexes and hydroformylation catalysis. *Catalysis Science & Technology*, 3(8), 1955-1963. <https://doi.org/10.1039/c3cy20665c>

General rights

It is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), other than for strictly personal, individual use, unless the work is under an open content license (like Creative Commons).

Disclaimer/Complaints regulations

If you believe that digital publication of certain material infringes any of your rights or (privacy) interests, please let the Library know, stating your reasons. In case of a legitimate complaint, the Library will make the material inaccessible and/or remove it from the website. Please Ask the Library: <https://uba.uva.nl/en/contact>, or a letter to: Library of the University of Amsterdam, Secretariat, Singel 425, 1012 WP Amsterdam, The Netherlands. You will be contacted as soon as possible.

UvA-DARE is a service provided by the library of the University of Amsterdam (<https://dare.uva.nl>)

Electronic Supplementary Material (ESI) for Catalysis Science & Technology
This journal is © The Royal Society of Chemistry 2013

Cambridge Crystallographic Data Centre
CCDC

This CIF contains data from an original supplementary publication
deposited with the CCDC, and may include chemical, crystal,
experimental, refinement, atomic coordinates,
anisotropic displacement parameters and molecular geometry data,
as required by the journal to which it was submitted.

This CIF is provided on the understanding that it is used for bona
fide research purposes only. It may contain copyright material
of the CCDC or of third parties, and may not be copied or further
disseminated in any form, whether machine-readable or not,
except for the purpose of generating routine backup copies
on your local computer system.

For further information on the CCDC, data deposition and
data retrieval see:
www.ccdc.cam.ac.uk

Bona fide researchers may freely download Mercury and enCIFer
from this site to visualise CIF-encoded structures and
to carry out CIF format checking respectively.

#####

data_s3343a
_database_code_depnum_ccdc_archive 'CCDC 831697'
#TrackingRef '5976_web_deposit_cif_file_0_AnthonyL.Spek_1309166038.s3343a.cif'

D.M.Tooke & A.L.Spek
Crystal & Structural Chemistry
Padualaan 8, 3584CH Utrecht, The Netherlands

Note: The dataset has only limited resolution, related to the
high disordered solvent volume (4203 out of 19962 cubic Angstrom)
The disordered solvent contribution to the structure factors was taken
into account with the SQUEEZE procedure (see data at the end of this CIF)

_audit_creation_method SHELXL-97
_chemical_name_systematic
;
?
;

_chemical_formula_moiety 'C99 H102 N9 O6 P Zn3'
_chemical_formula_sum 'C99 H102 N9 O6 P Zn3'
_chemical_formula_weight 1741.04

loop_
_atom_type_symbol
_atom_type_description
_atom_type_scatter_dispersion_real
_atom_type_scatter_dispersion_imag
_atom_type_scatter_source
C C 0.0033 0.0016 'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'
H H 0.0000 0.0000 'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'
N N 0.0061 0.0033 'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'
O O 0.0106 0.0060 'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'
P P 0.1023 0.0942 'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'
Zn Zn 0.2839 1.4301 'International Tables Vol C Tables 4.2.6.8 and 6.1.1.4'

_symmetry_cell_setting hexagonal
_symmetry_space_group_name_H-M 'P -3 c 1'
_symmetry_space_group_name_Hall '-P 3 2" c'

loop_
_symmetry_equiv_pos_as_xyz
'x, y, z'
'-y, x-y, z'
'-x+y, -x, z'
'y, x, -z+1/2'
'-x, -x+y, -z+1/2'
'x-y, -y, -z+1/2'
'-x, -y, -z'
'y, -x+y, -z'
'x-y, x, -z'
'-y, -x, z-1/2'
'x, x-y, z-1/2'
'-x+y, y, z-1/2'

_cell_length_a 20.8644(4)
_cell_length_b 20.8644(4)
_cell_length_c 52.9489(13)
_cell_angle_alpha 90.00
_cell_angle_beta 90.00
_cell_angle_gamma 120.00
_cell_volume 19961.8(7)
_cell_formula_units_Z 8
_cell_measurement_temperature 150(2)
_cell_measurement_reflns_used 237
_cell_measurement_theta_min 3.206
_cell_measurement_theta_max 13.675

_exptl_crystal_description block
_exptl_crystal_colour orange
_exptl_crystal_size_max 0.22
_exptl_crystal_size_mid 0.2
_exptl_crystal_size_min 0.14

```

_exptl_crystal_density_meas    ?
_exptl_crystal_density_diffn  1.159
_exptl_crystal_density_method  'not measured'
_exptl_crystal_F_000          7296
_exptl_absorpt_coefficient_mu  0.784
_exptl_absorpt_correction_type  multi-scan
_exptl_absorpt_correction_T_min 0.68
_exptl_absorpt_correction_T_max 0.9
_exptl_absorpt_process_details SADABS

```

```

_exptl_special_details
;
?
;

```

```

_diffn_ambient_temperature    150(2)
_diffn_radiation_wavelength    0.71073
_diffn_radiation_type          MoK\alpha
_diffn_radiation_source        'rotating anode'
_diffn_radiation_monochromator graphite
_diffn_measurement_device_type  'Nonius KappaCCD'
_diffn_measurement_method      'Omega and Phi scans'
_diffn_reflns_number           204945
_diffn_reflns_av_R_equivalents 0.0974
_diffn_reflns_av_sigmaI/netI   0.0355
_diffn_reflns_limit_h_min      -22
_diffn_reflns_limit_h_max      22
_diffn_reflns_limit_k_min      -22
_diffn_reflns_limit_k_max      22
_diffn_reflns_limit_l_min      -56
_diffn_reflns_limit_l_max      56
_diffn_reflns_theta_min        1.54
_diffn_reflns_theta_max        22.48
_reflns_number_total            8702
_reflns_number_gt               7387
_reflns_threshold_expression    I>2\sigma(I)

```

```

_computing_data_collection     'Nonius Collect'
_computing_cell_refinement      DIRAX
_computing_data_reduction      'EvalCCD and SADABS'
_computing_structure_solution   DIRDIF
_computing_structure_refinement 'SHELXL-97 (Sheldrick, 1997)'
_computing_molecular_graphics   PLATON
_computing_publication_material PLATON

```

```

_refine_special_details
;

```

Refinement of F^2 against ALL reflections. The weighted R-factor wR and goodness of fit S are based on F^2 , conventional R-factors R are based on F , with F set to zero for negative F^2 . The threshold expression of $F^2 > 2\sigma(F^2)$ is used only for calculating R-factors(gt) etc. and is not relevant to the choice of reflections for refinement. R-factors based on F^2 are statistically about twice as large as those based on F , and R-factors based on ALL data will be even larger.

;

_refine_ls_structure_factor_coef Fsqd
_refine_ls_matrix_type full
_refine_ls_weighting_scheme calc
_refine_ls_weighting_details
'calc w=1/[s^2^(Fo^2^)+(0.0502P)^2^+15.8981P] where P=(Fo^2^+2Fc^2^)/3'
_atom_sites_solution_primary direct
_atom_sites_solution_secondary difmap
_atom_sites_solution_hydrogens geom
_refine_ls_hydrogen_treatment constr
_refine_ls_extinction_method none
_refine_ls_extinction_coef ?
_refine_ls_number_reflns 8702
_refine_ls_number_parameters 722
_refine_ls_number_restraints 0
_refine_ls_R_factor_all 0.0746
_refine_ls_R_factor_gt 0.0538
_refine_ls_wR_factor_ref 0.1185
_refine_ls_wR_factor_gt 0.1105
_refine_ls_goodness_of_fit_ref 1.179
_refine_ls_restrained_S_all 1.179
_refine_ls_shift/su_max 0.001
_refine_ls_shift/su_mean 0.000

loop_
_atom_site_label
_atom_site_type_symbol
_atom_site_fract_x
_atom_site_fract_y
_atom_site_fract_z
_atom_site_U_iso_or_equiv
_atom_site_adp_type
_atom_site_occupancy
_atom_site_symmetry_multiplicity
_atom_site_calc_flag
_atom_site_refinement_flags
_atom_site_disorder_assembly
_atom_site_disorder_group
Zn1 Zn 0.31766(3) 0.13041(3) 0.063704(9) 0.04162(16) Uani 1 1 d . . .
P1 P 0.0000 0.0000 0.06459(4) 0.0423(5) Uani 1 3 d S . .
O1 O 0.29061(18) 0.03115(16) 0.07488(6) 0.0571(9) Uani 1 1 d . . .
O2 O 0.37079(16) 0.12938(15) 0.03333(6) 0.0460(7) Uani 1 1 d . . .
N1 N 0.21845(18) 0.11599(18) 0.04692(6) 0.0397(9) Uani 1 1 d . . .
N2 N 0.29275(19) 0.1530(2) 0.09973(7) 0.0445(9) Uani 1 1 d . . .
N3 N 0.37873(19) 0.24509(18) 0.06421(6) 0.0374(8) Uani 1 1 d . . .
C1 C 0.0868(2) 0.0667(2) 0.04862(7) 0.0382(10) Uani 1 1 d . . .
C2 C 0.0921(2) 0.1126(2) 0.02898(8) 0.0463(11) Uani 1 1 d . . .
H2 H 0.0490 0.1117 0.0226 0.056 Uiso 1 1 calc R . .
C3 C 0.1605(2) 0.1598(2) 0.01861(8) 0.0451(11) Uani 1 1 d . . .
H3 H 0.1650 0.1924 0.0053 0.054 Uiso 1 1 calc R . .
C4 C 0.2224(2) 0.1595(2) 0.02769(8) 0.0407(11) Uani 1 1 d . . .
H4 H 0.2690 0.1910 0.0201 0.049 Uiso 1 1 calc R . .
C5 C 0.1520(2) 0.0714(2) 0.05696(7) 0.0411(11) Uani 1 1 d . . .

H5 H 0.1491 0.0408 0.0707 0.049 Uiso 1 1 calc R . .
C6 C 0.3164(2) 0.2287(2) 0.10358(8) 0.0433(11) Uani 1 1 d . . .
C7 C 0.3618(2) 0.2775(2) 0.08467(8) 0.0393(11) Uani 1 1 d . . .
C8 C 0.3862(2) 0.3530(2) 0.08715(8) 0.0444(11) Uani 1 1 d . . .
H8 H 0.4159 0.3862 0.0742 0.053 Uiso 1 1 calc R . .
C9 C 0.3680(3) 0.3802(3) 0.10807(9) 0.0497(12) Uani 1 1 d . . .
H9 H 0.3859 0.4318 0.1097 0.060 Uiso 1 1 calc R . .
C10 C 0.3235(3) 0.3319(3) 0.12672(9) 0.0520(12) Uani 1 1 d . . .
H10 H 0.3109 0.3503 0.1412 0.062 Uiso 1 1 calc R . .
C11 C 0.2976(2) 0.2574(3) 0.12430(9) 0.0507(12) Uani 1 1 d . . .
H11 H 0.2661 0.2246 0.1370 0.061 Uiso 1 1 calc R . .
C12 C 0.2555(2) 0.1021(3) 0.11641(9) 0.0515(12) Uani 1 1 d . . .
H12 H 0.2452 0.1177 0.1320 0.062 Uiso 1 1 calc R . .
C13 C 0.2283(3) 0.0240(3) 0.11338(9) 0.0527(13) Uani 1 1 d . . .
C14 C 0.1809(3) -0.0213(3) 0.13291(10) 0.0733(16) Uani 1 1 d . . .
H14 H 0.1704 0.0006 0.1469 0.088 Uiso 1 1 calc R . .
C15 C 0.1503(3) -0.0964(3) 0.13174(12) 0.0807(18) Uani 1 1 d . . .
H15 H 0.1183 -0.1269 0.1448 0.097 Uiso 1 1 calc R . .
C16 C 0.1662(3) -0.1275(3) 0.11127(11) 0.0775(17) Uani 1 1 d . . .
H16 H 0.1434 -0.1799 0.1107 0.093 Uiso 1 1 calc R . .
C17 C 0.2126(3) -0.0880(3) 0.09190(10) 0.0606(14) Uani 1 1 d . . .
C18 C 0.2456(3) -0.0078(3) 0.09268(9) 0.0538(13) Uani 1 1 d . . .
C19 C 0.4284(2) 0.2845(2) 0.04761(8) 0.0405(11) Uani 1 1 d . . .
H19 H 0.4524 0.3366 0.0498 0.049 Uiso 1 1 calc R . .
C20 C 0.4517(2) 0.2586(2) 0.02620(8) 0.0382(10) Uani 1 1 d . . .
C21 C 0.4234(2) 0.1817(2) 0.02039(8) 0.0395(11) Uani 1 1 d . . .
C22 C 0.4562(2) 0.1638(2) -0.00045(8) 0.0439(11) Uani 1 1 d . . .
C23 C 0.5114(3) 0.2207(3) -0.01391(9) 0.0543(13) Uani 1 1 d . . .
H23 H 0.5327 0.2086 -0.0276 0.065 Uiso 1 1 calc R . .
C24 C 0.5382(3) 0.2956(3) -0.00864(9) 0.0578(13) Uani 1 1 d . . .
H24 H 0.5761 0.3330 -0.0187 0.069 Uiso 1 1 calc R . .
C25 C 0.5090(2) 0.3140(2) 0.01127(9) 0.0502(12) Uani 1 1 d . . .
H25 H 0.5273 0.3647 0.0152 0.060 Uiso 1 1 calc R . .
C26 C 0.2290(4) -0.1248(3) 0.06976(10) 0.0730(17) Uani 1 1 d . . .
C27 C 0.3109(4) -0.0996(3) 0.06839(11) 0.0825(18) Uani 1 1 d . . .
H27A H 0.3394 -0.0457 0.0665 0.124 Uiso 1 1 calc R . .
H27B H 0.3202 -0.1229 0.0538 0.124 Uiso 1 1 calc R . .
H27C H 0.3261 -0.1140 0.0839 0.124 Uiso 1 1 calc R . .
C28 C 0.2027(4) -0.1062(3) 0.04467(10) 0.090(2) Uani 1 1 d . . .
H28A H 0.2331 -0.0532 0.0411 0.134 Uiso 1 1 calc R . .
H28B H 0.1508 -0.1193 0.0463 0.134 Uiso 1 1 calc R . .
H28C H 0.2077 -0.1345 0.0308 0.134 Uiso 1 1 calc R . .
C29 C 0.1853(4) -0.2104(3) 0.07271(11) 0.107(2) Uani 1 1 d . . .
H29A H 0.1903 -0.2334 0.0572 0.160 Uiso 1 1 calc R . .
H29B H 0.1330 -0.2271 0.0757 0.160 Uiso 1 1 calc R . .
H29C H 0.2053 -0.2247 0.0870 0.160 Uiso 1 1 calc R . .
C30 C 0.4296(2) 0.0825(2) -0.00686(9) 0.0486(12) Uani 1 1 d . . .
C31 C 0.4725(3) 0.0754(3) -0.02935(9) 0.0588(13) Uani 1 1 d . . .
H31A H 0.4643 0.0978 -0.0444 0.088 Uiso 1 1 calc R . .
H31B H 0.4550 0.0230 -0.0326 0.088 Uiso 1 1 calc R . .
H31C H 0.5255 0.1009 -0.0254 0.088 Uiso 1 1 calc R . .
C32 C 0.4408(3) 0.0430(2) 0.01599(9) 0.0544(13) Uani 1 1 d . . .
H32A H 0.4936 0.0671 0.0202 0.082 Uiso 1 1 calc R . .
H32B H 0.4227 -0.0090 0.0118 0.082 Uiso 1 1 calc R . .

H32C H 0.4132 0.0458 0.0305 0.082 Uiso 1 1 calc R . .
 C33 C 0.3472(3) 0.0415(2) -0.01374(9) 0.0595(14) Uani 1 1 d . . .
 H33A H 0.3183 0.0419 0.0008 0.089 Uiso 1 1 calc R . .
 H33B H 0.3317 -0.0097 -0.0183 0.089 Uiso 1 1 calc R . .
 H33C H 0.3391 0.0662 -0.0281 0.089 Uiso 1 1 calc R . .
 Zn2 Zn 0.49323(2) 0.40640(2) 0.157649(8) 0.03040(14) Uani 1 1 d . . .
 P2 P 0.6667 0.3333 0.22641(3) 0.0304(4) Uani 1 3 d S . .
 O3 O 0.42090(14) 0.31669(14) 0.17585(5) 0.0374(7) Uani 1 1 d . . .
 O4 O 0.45485(14) 0.47001(15) 0.16918(5) 0.0380(7) Uani 1 1 d . . .
 N4 N 0.57960(17) 0.43703(17) 0.18412(5) 0.0305(8) Uani 1 1 d . . .
 N5 N 0.50678(17) 0.34098(18) 0.13121(5) 0.0294(8) Uani 1 1 d . . .
 N6 N 0.54737(17) 0.48347(18) 0.12849(5) 0.0321(8) Uani 1 1 d . . .
 C34 C 0.6479(2) 0.4016(2) 0.21179(7) 0.0276(9) Uani 1 1 d . . .
 C35 C 0.5973(2) 0.3872(2) 0.19264(7) 0.0300(9) Uani 1 1 d . . .
 H35 H 0.5738 0.3395 0.1851 0.036 Uiso 1 1 calc R . .
 C36 C 0.6130(2) 0.5040(2) 0.19478(7) 0.0364(10) Uani 1 1 d . . .
 H36 H 0.6004 0.5395 0.1891 0.044 Uiso 1 1 calc R . .
 C37 C 0.6651(2) 0.5239(2) 0.21383(8) 0.0412(11) Uani 1 1 d . . .
 H37 H 0.6885 0.5722 0.2208 0.049 Uiso 1 1 calc R . .
 C38 C 0.6822(2) 0.4722(2) 0.22232(7) 0.0351(10) Uani 1 1 d . . .
 H38 H 0.7175 0.4846 0.2355 0.042 Uiso 1 1 calc R . .
 C39 C 0.5496(2) 0.3804(2) 0.10981(7) 0.0301(9) Uani 1 1 d . . .
 C40 C 0.5686(2) 0.3487(2) 0.09016(7) 0.0389(10) Uani 1 1 d . . .
 H40 H 0.5539 0.2976 0.0908 0.047 Uiso 1 1 calc R . .
 C41 C 0.6085(2) 0.3908(3) 0.06971(7) 0.0422(11) Uani 1 1 d . . .
 H41 H 0.6205 0.3684 0.0563 0.051 Uiso 1 1 calc R . .
 C42 C 0.6312(2) 0.4651(3) 0.06866(8) 0.0427(11) Uani 1 1 d . . .
 H42 H 0.6593 0.4938 0.0546 0.051 Uiso 1 1 calc R . .
 C43 C 0.6135(2) 0.4976(2) 0.08775(7) 0.0407(11) Uani 1 1 d . . .
 H43 H 0.6293 0.5489 0.0869 0.049 Uiso 1 1 calc R . .
 C44 C 0.5723(2) 0.4563(2) 0.10849(7) 0.0310(10) Uani 1 1 d . . .
 C45 C 0.4761(2) 0.2696(2) 0.13275(7) 0.0339(10) Uani 1 1 d . . .
 H45 H 0.4876 0.2458 0.1196 0.041 Uiso 1 1 calc R . .
 C46 C 0.4265(2) 0.2223(2) 0.15214(7) 0.0317(9) Uani 1 1 d . . .
 C47 C 0.3989(2) 0.2472(2) 0.17216(7) 0.0324(10) Uani 1 1 d . . .
 C48 C 0.3430(2) 0.1926(2) 0.18854(7) 0.0362(10) Uani 1 1 d . . .
 C49 C 0.3206(2) 0.1194(2) 0.18418(8) 0.0452(11) Uani 1 1 d . . .
 H49 H 0.2836 0.0834 0.1949 0.054 Uiso 1 1 calc R . .
 C50 C 0.3491(2) 0.0949(2) 0.16496(8) 0.0448(11) Uani 1 1 d . . .
 H50 H 0.3325 0.0437 0.1629 0.054 Uiso 1 1 calc R . .
 C51 C 0.4012(2) 0.1461(2) 0.14925(8) 0.0405(11) Uani 1 1 d . . .
 H51 H 0.4208 0.1302 0.1361 0.049 Uiso 1 1 calc R . .
 C52 C 0.5614(2) 0.5509(2) 0.12905(7) 0.0403(11) Uani 1 1 d . . .
 H52 H 0.5921 0.5827 0.1160 0.048 Uiso 1 1 calc R . .
 C53 C 0.5351(2) 0.5827(2) 0.14742(8) 0.0419(11) Uani 1 1 d . . .
 C54 C 0.5634(3) 0.6603(3) 0.14526(9) 0.0619(14) Uani 1 1 d . . .
 H54 H 0.5987 0.6880 0.1326 0.074 Uiso 1 1 calc R . .
 C55 C 0.5397(3) 0.6947(3) 0.16145(10) 0.0769(17) Uani 1 1 d . . .
 H55 H 0.5593 0.7467 0.1603 0.092 Uiso 1 1 calc R . .
 C56 C 0.4866(3) 0.6536(3) 0.17982(10) 0.0657(15) Uani 1 1 d . . .
 H56 H 0.4700 0.6788 0.1906 0.079 Uiso 1 1 calc R . .
 C57 C 0.4570(2) 0.5784(2) 0.18305(8) 0.0436(11) Uani 1 1 d . . .
 C58 C 0.4817(2) 0.5408(2) 0.16642(7) 0.0368(10) Uani 1 1 d . . .
 C59 C 0.3106(2) 0.2168(2) 0.21010(8) 0.0458(11) Uani 1 1 d . . .

C60 C 0.3728(3) 0.2660(3) 0.22866(8) 0.0567(13) Uani 1 1 d . . .
 H60A H 0.3950 0.2381 0.2356 0.085 Uiso 1 1 calc R . .
 H60B H 0.3522 0.2816 0.2424 0.085 Uiso 1 1 calc R . .
 H60C H 0.4107 0.3098 0.2198 0.085 Uiso 1 1 calc R . .
 C61 C 0.2509(3) 0.1500(3) 0.22466(9) 0.0661(15) Uani 1 1 d . . .
 H61A H 0.2726 0.1219 0.2319 0.099 Uiso 1 1 calc R . .
 H61B H 0.2108 0.1182 0.2131 0.099 Uiso 1 1 calc R . .
 H61C H 0.2313 0.1673 0.2382 0.099 Uiso 1 1 calc R . .
 C62 C 0.2737(3) 0.2591(3) 0.19945(9) 0.0585(13) Uani 1 1 d . . .
 H62A H 0.2544 0.2754 0.2134 0.088 Uiso 1 1 calc R . .
 H62B H 0.2330 0.2266 0.1882 0.088 Uiso 1 1 calc R . .
 H62C H 0.3103 0.3024 0.1900 0.088 Uiso 1 1 calc R . .
 C63 C 0.4011(3) 0.5347(2) 0.20415(8) 0.0497(12) Uani 1 1 d . . .
 C64 C 0.3801(3) 0.5841(3) 0.21910(10) 0.0745(16) Uani 1 1 d . . .
 H64A H 0.3591 0.6057 0.2076 0.112 Uiso 1 1 calc R . .
 H64B H 0.4243 0.6238 0.2273 0.112 Uiso 1 1 calc R . .
 H64C H 0.3434 0.5545 0.2320 0.112 Uiso 1 1 calc R . .
 C65 C 0.4352(3) 0.5033(3) 0.22250(8) 0.0618(14) Uani 1 1 d . . .
 H65A H 0.3996 0.4758 0.2359 0.093 Uiso 1 1 calc R . .
 H65B H 0.4802 0.5440 0.2299 0.093 Uiso 1 1 calc R . .
 H65C H 0.4476 0.4701 0.2134 0.093 Uiso 1 1 calc R . .
 C66 C 0.3296(3) 0.4724(3) 0.19292(10) 0.0644(14) Uani 1 1 d . . .
 H66A H 0.3074 0.4934 0.1817 0.097 Uiso 1 1 calc R . .
 H66B H 0.2950 0.4448 0.2066 0.097 Uiso 1 1 calc R . .
 H66C H 0.3406 0.4390 0.1832 0.097 Uiso 1 1 calc R . .

loop_

_atom_site_aniso_label
 _atom_site_aniso_U_11
 _atom_site_aniso_U_22
 _atom_site_aniso_U_33
 _atom_site_aniso_U_23
 _atom_site_aniso_U_13
 _atom_site_aniso_U_12

Zn1 0.0411(3) 0.0319(3) 0.0487(3) -0.0026(2) -0.0127(2) 0.0159(2)
 P1 0.0439(8) 0.0439(8) 0.0392(11) 0.000 0.000 0.0219(4)
 O1 0.071(2) 0.0351(18) 0.058(2) 0.0058(16) -0.0005(18) 0.0210(17)
 O2 0.0446(19) 0.0322(17) 0.060(2) -0.0052(15) -0.0054(16) 0.0180(16)
 N1 0.037(2) 0.036(2) 0.043(2) -0.0043(18) -0.0083(17) 0.0162(19)
 N2 0.045(2) 0.038(2) 0.047(2) -0.0032(19) -0.0138(19) 0.0178(19)
 N3 0.038(2) 0.032(2) 0.044(2) -0.0035(18) -0.0128(18) 0.0186(18)
 C1 0.039(3) 0.041(3) 0.036(2) -0.006(2) -0.007(2) 0.021(2)
 C2 0.042(3) 0.052(3) 0.045(3) -0.004(2) -0.010(2) 0.023(2)
 C3 0.042(3) 0.049(3) 0.038(3) 0.003(2) -0.004(2) 0.018(2)
 C4 0.035(3) 0.040(3) 0.039(3) -0.007(2) -0.008(2) 0.013(2)
 C5 0.049(3) 0.034(3) 0.035(2) -0.003(2) -0.009(2) 0.016(2)
 C6 0.043(3) 0.048(3) 0.041(3) -0.011(2) -0.016(2) 0.025(2)
 C7 0.039(3) 0.042(3) 0.042(3) -0.009(2) -0.016(2) 0.024(2)
 C8 0.051(3) 0.043(3) 0.046(3) -0.007(2) -0.016(2) 0.028(2)
 C9 0.054(3) 0.048(3) 0.055(3) -0.015(3) -0.021(3) 0.031(3)
 C10 0.052(3) 0.065(4) 0.050(3) -0.017(3) -0.015(3) 0.037(3)
 C11 0.046(3) 0.056(3) 0.049(3) 0.000(2) -0.009(2) 0.024(3)
 C12 0.049(3) 0.055(3) 0.046(3) -0.002(3) -0.013(2) 0.023(3)
 C13 0.047(3) 0.043(3) 0.053(3) 0.013(3) -0.010(2) 0.011(2)

C14 0.064(4) 0.066(4) 0.069(4) 0.006(3) -0.004(3) 0.017(3)
 C15 0.078(4) 0.057(4) 0.077(4) 0.019(3) 0.008(3) 0.011(3)
 C16 0.079(4) 0.043(3) 0.078(4) 0.002(3) -0.018(3) 0.007(3)
 C17 0.066(3) 0.036(3) 0.059(3) 0.007(3) -0.021(3) 0.010(3)
 C18 0.052(3) 0.051(3) 0.048(3) -0.001(3) -0.019(3) 0.018(3)
 C19 0.039(3) 0.032(2) 0.052(3) -0.004(2) -0.016(2) 0.019(2)
 C20 0.042(3) 0.034(3) 0.041(3) -0.003(2) -0.009(2) 0.021(2)
 C21 0.033(3) 0.031(3) 0.053(3) -0.004(2) -0.016(2) 0.016(2)
 C22 0.042(3) 0.044(3) 0.053(3) -0.010(2) -0.013(2) 0.027(2)
 C23 0.049(3) 0.057(3) 0.058(3) -0.012(3) -0.002(3) 0.027(3)
 C24 0.056(3) 0.042(3) 0.063(3) -0.006(3) 0.002(3) 0.016(3)
 C25 0.054(3) 0.032(3) 0.059(3) -0.006(2) -0.005(3) 0.018(2)
 C26 0.110(5) 0.034(3) 0.054(3) -0.001(2) -0.016(3) 0.020(3)
 C27 0.115(5) 0.061(4) 0.074(4) -0.001(3) -0.007(4) 0.045(4)
 C28 0.126(5) 0.056(4) 0.061(4) -0.008(3) -0.033(4) 0.026(4)
 C29 0.166(7) 0.037(3) 0.087(4) 0.000(3) -0.007(4) 0.028(4)
 C30 0.054(3) 0.044(3) 0.057(3) -0.011(2) -0.020(2) 0.030(2)
 C31 0.069(3) 0.056(3) 0.065(3) -0.017(3) -0.016(3) 0.041(3)
 C32 0.061(3) 0.040(3) 0.072(3) -0.013(2) -0.017(3) 0.032(3)
 C33 0.060(3) 0.048(3) 0.074(3) -0.020(3) -0.029(3) 0.030(3)
 Zn2 0.0345(3) 0.0331(3) 0.0271(3) -0.0024(2) 0.0000(2) 0.0195(2)
 P2 0.0326(6) 0.0326(6) 0.0258(10) 0.000 0.000 0.0163(3)
 O3 0.0417(17) 0.0347(17) 0.0359(16) -0.0033(13) 0.0065(13) 0.0191(14)
 O4 0.0419(17) 0.0381(18) 0.0405(17) -0.0014(13) 0.0032(13) 0.0249(15)
 N4 0.0332(19) 0.030(2) 0.0293(18) -0.0043(16) -0.0007(15) 0.0164(17)
 N5 0.0295(19) 0.033(2) 0.0280(18) -0.0034(15) -0.0006(15) 0.0173(16)
 N6 0.039(2) 0.034(2) 0.0286(18) -0.0002(15) -0.0027(15) 0.0215(17)
 C34 0.031(2) 0.033(2) 0.021(2) 0.0001(17) 0.0038(18) 0.0168(19)
 C35 0.033(2) 0.029(2) 0.028(2) -0.0038(18) 0.0017(19) 0.016(2)
 C36 0.040(3) 0.034(3) 0.038(2) 0.004(2) 0.005(2) 0.021(2)
 C37 0.048(3) 0.032(2) 0.038(3) -0.006(2) -0.010(2) 0.016(2)
 C38 0.036(2) 0.036(3) 0.029(2) -0.0041(19) -0.0113(19) 0.015(2)
 C39 0.026(2) 0.044(3) 0.024(2) -0.0036(19) -0.0044(18) 0.020(2)
 C40 0.038(3) 0.045(3) 0.034(2) -0.007(2) 0.002(2) 0.021(2)
 C41 0.037(3) 0.065(3) 0.030(2) -0.009(2) 0.002(2) 0.029(2)
 C42 0.038(3) 0.062(3) 0.032(2) 0.011(2) 0.005(2) 0.027(2)
 C43 0.043(3) 0.047(3) 0.037(3) 0.004(2) 0.005(2) 0.027(2)
 C44 0.030(2) 0.042(3) 0.025(2) -0.0034(19) -0.0047(18) 0.021(2)
 C45 0.035(2) 0.041(3) 0.034(2) -0.012(2) -0.008(2) 0.024(2)
 C46 0.032(2) 0.037(3) 0.029(2) -0.0020(19) -0.0023(19) 0.019(2)
 C47 0.030(2) 0.037(3) 0.032(2) -0.004(2) -0.0051(19) 0.018(2)
 C48 0.034(2) 0.036(3) 0.036(2) 0.002(2) 0.000(2) 0.016(2)
 C49 0.039(3) 0.044(3) 0.043(3) 0.007(2) 0.003(2) 0.013(2)
 C50 0.057(3) 0.027(2) 0.046(3) -0.002(2) -0.005(2) 0.018(2)
 C51 0.051(3) 0.041(3) 0.036(2) -0.005(2) -0.003(2) 0.028(2)
 C52 0.050(3) 0.040(3) 0.032(2) 0.005(2) 0.001(2) 0.023(2)
 C53 0.053(3) 0.038(3) 0.040(3) -0.004(2) 0.001(2) 0.027(2)
 C54 0.084(4) 0.048(3) 0.055(3) 0.003(3) 0.017(3) 0.035(3)
 C55 0.116(5) 0.041(3) 0.079(4) -0.002(3) 0.028(4) 0.042(3)
 C56 0.089(4) 0.050(3) 0.069(4) -0.005(3) 0.020(3) 0.043(3)
 C57 0.059(3) 0.039(3) 0.043(3) -0.006(2) -0.001(2) 0.032(2)
 C58 0.043(3) 0.038(3) 0.038(2) -0.006(2) -0.004(2) 0.026(2)
 C59 0.046(3) 0.050(3) 0.040(3) 0.004(2) 0.012(2) 0.023(2)
 C60 0.067(3) 0.070(3) 0.038(3) -0.010(2) 0.004(2) 0.037(3)

C61 0.068(4) 0.066(3) 0.057(3) 0.013(3) 0.030(3) 0.028(3)
 C62 0.049(3) 0.074(4) 0.063(3) 0.007(3) 0.017(2) 0.038(3)
 C63 0.053(3) 0.048(3) 0.052(3) -0.012(2) 0.008(2) 0.028(3)
 C64 0.084(4) 0.068(4) 0.076(4) -0.017(3) 0.021(3) 0.042(3)
 C65 0.067(3) 0.076(4) 0.041(3) 0.008(3) 0.012(3) 0.035(3)
 C66 0.045(3) 0.063(3) 0.088(4) -0.013(3) 0.010(3) 0.029(3)

_geom_special_details

;
 All esds (except the esd in the dihedral angle between two l.s. planes)
 are estimated using the full covariance matrix. The cell esds are taken
 into account individually in the estimation of esds in distances, angles
 and torsion angles; correlations between esds in cell parameters are only
 used when they are defined by crystal symmetry. An approximate (isotropic)
 treatment of cell esds is used for estimating esds involving l.s. planes.

;

loop_

_geom_bond_atom_site_label_1

_geom_bond_atom_site_label_2

_geom_bond_distance

_geom_bond_site_symmetry_2

_geom_bond_publ_flag

Zn1 O1 1.947(3) . ?

Zn1 O2 1.960(3) . ?

Zn1 N3 2.074(3) . ?

Zn1 N2 2.092(4) . ?

Zn1 N1 2.131(3) . ?

P1 C1 1.847(4) 2 ?

P1 C1 1.847(4) . ?

P1 C1 1.847(4) 3 ?

O1 C18 1.291(5) . ?

O2 C21 1.291(5) . ?

N1 C5 1.335(5) . ?

N1 C4 1.339(5) . ?

N2 C12 1.298(5) . ?

N2 C6 1.415(5) . ?

N3 C19 1.293(5) . ?

N3 C7 1.413(5) . ?

C1 C2 1.380(6) . ?

C1 C5 1.386(5) . ?

C2 C3 1.380(6) . ?

C2 H2 0.9500 . ?

C3 C4 1.380(6) . ?

C3 H3 0.9500 . ?

C4 H4 0.9500 . ?

C5 H5 0.9500 . ?

C6 C11 1.397(6) . ?

C6 C7 1.404(6) . ?

C7 C8 1.398(6) . ?

C8 C9 1.382(6) . ?

C8 H8 0.9500 . ?

C9 C10 1.385(6) . ?

C9 H9 0.9500 . ?

C10 C11 1.373(6) . ?
C10 H10 0.9500 . ?
C11 H11 0.9500 . ?
C12 C13 1.442(6) . ?
C12 H12 0.9500 . ?
C13 C14 1.417(7) . ?
C13 C18 1.419(7) . ?
C14 C15 1.365(7) . ?
C14 H14 0.9500 . ?
C15 C16 1.388(8) . ?
C15 H15 0.9500 . ?
C16 C17 1.368(7) . ?
C16 H16 0.9500 . ?
C17 C18 1.456(6) . ?
C17 C26 1.531(7) . ?
C19 C20 1.440(6) . ?
C19 H19 0.9500 . ?
C20 C25 1.417(6) . ?
C20 C21 1.440(5) . ?
C21 C22 1.443(6) . ?
C22 C23 1.370(6) . ?
C22 C30 1.537(6) . ?
C23 C24 1.400(6) . ?
C23 H23 0.9500 . ?
C24 C25 1.365(6) . ?
C24 H24 0.9500 . ?
C25 H25 0.9500 . ?
C26 C27 1.519(8) . ?
C26 C29 1.555(7) . ?
C26 C28 1.558(7) . ?
C27 H27A 0.9800 . ?
C27 H27B 0.9800 . ?
C27 H27C 0.9800 . ?
C28 H28A 0.9800 . ?
C28 H28B 0.9800 . ?
C28 H28C 0.9800 . ?
C29 H29A 0.9800 . ?
C29 H29B 0.9800 . ?
C29 H29C 0.9800 . ?
C30 C33 1.533(6) . ?
C30 C31 1.541(6) . ?
C30 C32 1.545(6) . ?
C31 H31A 0.9800 . ?
C31 H31B 0.9800 . ?
C31 H31C 0.9800 . ?
C32 H32A 0.9800 . ?
C32 H32B 0.9800 . ?
C32 H32C 0.9800 . ?
C33 H33A 0.9800 . ?
C33 H33B 0.9800 . ?
C33 H33C 0.9800 . ?
Zn2 O4 1.959(3) . ?
Zn2 O3 1.971(3) . ?
Zn2 N5 2.071(3) . ?

Zn2 N6 2.105(3) . ?
Zn2 N4 2.114(3) . ?
P2 C34 1.826(4) . ?
P2 C34 1.827(4) 3_665 ?
P2 C34 1.827(4) 2_655 ?
O3 C47 1.298(4) . ?
O4 C58 1.300(5) . ?
N4 C36 1.335(5) . ?
N4 C35 1.344(5) . ?
N5 C45 1.297(5) . ?
N5 C39 1.423(5) . ?
N6 C52 1.286(5) . ?
N6 C44 1.417(5) . ?
C34 C35 1.384(5) . ?
C34 C38 1.393(5) . ?
C35 H35 0.9500 . ?
C36 C37 1.386(5) . ?
C36 H36 0.9500 . ?
C37 C38 1.369(5) . ?
C37 H37 0.9500 . ?
C38 H38 0.9500 . ?
C39 C40 1.392(5) . ?
C39 C44 1.410(5) . ?
C40 C41 1.381(6) . ?
C40 H40 0.9500 . ?
C41 C42 1.377(6) . ?
C41 H41 0.9500 . ?
C42 C43 1.368(6) . ?
C42 H42 0.9500 . ?
C43 C44 1.395(5) . ?
C43 H43 0.9500 . ?
C45 C46 1.441(5) . ?
C45 H45 0.9500 . ?
C46 C51 1.412(5) . ?
C46 C47 1.422(5) . ?
C47 C48 1.443(5) . ?
C48 C49 1.375(6) . ?
C48 C59 1.534(6) . ?
C49 C50 1.398(6) . ?
C49 H49 0.9500 . ?
C50 C51 1.361(6) . ?
C50 H50 0.9500 . ?
C51 H51 0.9500 . ?
C52 C53 1.432(6) . ?
C52 H52 0.9500 . ?
C53 C54 1.424(6) . ?
C53 C58 1.429(6) . ?
C54 C55 1.359(6) . ?
C54 H54 0.9500 . ?
C55 C56 1.401(7) . ?
C55 H55 0.9500 . ?
C56 C57 1.381(6) . ?
C56 H56 0.9500 . ?
C57 C58 1.435(5) . ?

C57 C63 1.541(6) . ?
C59 C61 1.533(6) . ?
C59 C62 1.539(6) . ?
C59 C60 1.540(6) . ?
C60 H60A 0.9800 . ?
C60 H60B 0.9800 . ?
C60 H60C 0.9800 . ?
C61 H61A 0.9800 . ?
C61 H61B 0.9800 . ?
C61 H61C 0.9800 . ?
C62 H62A 0.9800 . ?
C62 H62B 0.9800 . ?
C62 H62C 0.9800 . ?
C63 C66 1.527(6) . ?
C63 C64 1.528(6) . ?
C63 C65 1.531(6) . ?
C64 H64A 0.9800 . ?
C64 H64B 0.9800 . ?
C64 H64C 0.9800 . ?
C65 H65A 0.9800 . ?
C65 H65B 0.9800 . ?
C65 H65C 0.9800 . ?
C66 H66A 0.9800 . ?
C66 H66B 0.9800 . ?
C66 H66C 0.9800 . ?

loop_
_geom_angle_atom_site_label_1
_geom_angle_atom_site_label_2
_geom_angle_atom_site_label_3
_geom_angle
_geom_angle_site_symmetry_1
_geom_angle_site_symmetry_3
_geom_angle_publ_flag
O1 Zn1 O2 95.89(13) . . ?
O1 Zn1 N3 155.18(13) . . ?
O2 Zn1 N3 89.92(13) . . ?
O1 Zn1 N2 89.41(14) . . ?
O2 Zn1 N2 163.05(13) . . ?
N3 Zn1 N2 78.87(14) . . ?
O1 Zn1 N1 103.42(13) . . ?
O2 Zn1 N1 99.85(12) . . ?
N3 Zn1 N1 99.29(13) . . ?
N2 Zn1 N1 94.53(13) . . ?
C1 P1 C1 100.69(16) 2 . ?
C1 P1 C1 100.69(16) 2 3 ?
C1 P1 C1 100.70(16) . 3 ?
C18 O1 Zn1 128.7(3) . . ?
C21 O2 Zn1 132.3(3) . . ?
C5 N1 C4 117.7(4) . . ?
C5 N1 Zn1 122.0(3) . . ?
C4 N1 Zn1 119.7(3) . . ?
C12 N2 C6 123.2(4) . . ?
C12 N2 Zn1 123.4(3) . . ?

C6 N2 Zn1 113.3(3) . . ?
 C19 N3 C7 122.0(4) . . ?
 C19 N3 Zn1 124.0(3) . . ?
 C7 N3 Zn1 114.0(3) . . ?
 C2 C1 C5 117.1(4) . . ?
 C2 C1 P1 125.2(3) . . ?
 C5 C1 P1 117.7(3) . . ?
 C3 C2 C1 119.4(4) . . ?
 C3 C2 H2 120.3 . . ?
 C1 C2 H2 120.3 . . ?
 C2 C3 C4 119.6(4) . . ?
 C2 C3 H3 120.2 . . ?
 C4 C3 H3 120.2 . . ?
 N1 C4 C3 121.9(4) . . ?
 N1 C4 H4 119.1 . . ?
 C3 C4 H4 119.1 . . ?
 N1 C5 C1 124.3(4) . . ?
 N1 C5 H5 117.9 . . ?
 C1 C5 H5 117.9 . . ?
 C11 C6 C7 118.8(4) . . ?
 C11 C6 N2 125.2(4) . . ?
 C7 C6 N2 116.1(4) . . ?
 C8 C7 C6 119.0(4) . . ?
 C8 C7 N3 125.0(4) . . ?
 C6 C7 N3 116.0(4) . . ?
 C9 C8 C7 121.1(4) . . ?
 C9 C8 H8 119.4 . . ?
 C7 C8 H8 119.4 . . ?
 C8 C9 C10 119.7(4) . . ?
 C8 C9 H9 120.1 . . ?
 C10 C9 H9 120.1 . . ?
 C11 C10 C9 119.9(4) . . ?
 C11 C10 H10 120.1 . . ?
 C9 C10 H10 120.1 . . ?
 C10 C11 C6 121.5(5) . . ?
 C10 C11 H11 119.2 . . ?
 C6 C11 H11 119.2 . . ?
 N2 C12 C13 125.8(4) . . ?
 N2 C12 H12 117.1 . . ?
 C13 C12 H12 117.1 . . ?
 C14 C13 C18 120.5(5) . . ?
 C14 C13 C12 114.9(5) . . ?
 C18 C13 C12 124.6(4) . . ?
 C15 C14 C13 120.2(6) . . ?
 C15 C14 H14 119.9 . . ?
 C13 C14 H14 119.9 . . ?
 C14 C15 C16 119.2(5) . . ?
 C14 C15 H15 120.4 . . ?
 C16 C15 H15 120.4 . . ?
 C17 C16 C15 124.5(5) . . ?
 C17 C16 H16 117.8 . . ?
 C15 C16 H16 117.8 . . ?
 C16 C17 C18 117.2(5) . . ?
 C16 C17 C26 122.7(5) . . ?

C18 C17 C26 120.2(5) . . ?
O1 C18 C13 122.9(4) . . ?
O1 C18 C17 118.7(5) . . ?
C13 C18 C17 118.4(5) . . ?
N3 C19 C20 127.6(4) . . ?
N3 C19 H19 116.2 . . ?
C20 C19 H19 116.2 . . ?
C25 C20 C21 119.9(4) . . ?
C25 C20 C19 116.0(4) . . ?
C21 C20 C19 124.0(4) . . ?
O2 C21 C20 122.0(4) . . ?
O2 C21 C22 120.0(4) . . ?
C20 C21 C22 117.9(4) . . ?
C23 C22 C21 118.5(4) . . ?
C23 C22 C30 121.7(4) . . ?
C21 C22 C30 119.9(4) . . ?
C22 C23 C24 123.9(5) . . ?
C22 C23 H23 118.1 . . ?
C24 C23 H23 118.1 . . ?
C25 C24 C23 118.8(5) . . ?
C25 C24 H24 120.6 . . ?
C23 C24 H24 120.6 . . ?
C24 C25 C20 121.0(4) . . ?
C24 C25 H25 119.5 . . ?
C20 C25 H25 119.5 . . ?
C27 C26 C17 111.0(4) . . ?
C27 C26 C29 108.3(5) . . ?
C17 C26 C29 110.5(5) . . ?
C27 C26 C28 110.4(5) . . ?
C17 C26 C28 109.5(5) . . ?
C29 C26 C28 107.1(4) . . ?
C26 C27 H27A 109.5 . . ?
C26 C27 H27B 109.5 . . ?
H27A C27 H27B 109.5 . . ?
C26 C27 H27C 109.5 . . ?
H27A C27 H27C 109.5 . . ?
H27B C27 H27C 109.5 . . ?
C26 C28 H28A 109.5 . . ?
C26 C28 H28B 109.5 . . ?
H28A C28 H28B 109.5 . . ?
C26 C28 H28C 109.5 . . ?
H28A C28 H28C 109.5 . . ?
H28B C28 H28C 109.5 . . ?
C26 C29 H29A 109.5 . . ?
C26 C29 H29B 109.5 . . ?
H29A C29 H29B 109.5 . . ?
C26 C29 H29C 109.5 . . ?
H29A C29 H29C 109.5 . . ?
H29B C29 H29C 109.5 . . ?
C33 C30 C22 110.6(3) . . ?
C33 C30 C31 107.8(4) . . ?
C22 C30 C31 111.7(4) . . ?
C33 C30 C32 108.4(4) . . ?
C22 C30 C32 110.4(3) . . ?

C31 C30 C32 107.7(4) . . ?
 C30 C31 H31A 109.5 . . ?
 C30 C31 H31B 109.5 . . ?
 H31A C31 H31B 109.5 . . ?
 C30 C31 H31C 109.5 . . ?
 H31A C31 H31C 109.5 . . ?
 H31B C31 H31C 109.5 . . ?
 C30 C32 H32A 109.5 . . ?
 C30 C32 H32B 109.5 . . ?
 H32A C32 H32B 109.5 . . ?
 C30 C32 H32C 109.5 . . ?
 H32A C32 H32C 109.5 . . ?
 H32B C32 H32C 109.5 . . ?
 C30 C33 H33A 109.5 . . ?
 C30 C33 H33B 109.5 . . ?
 H33A C33 H33B 109.5 . . ?
 C30 C33 H33C 109.5 . . ?
 H33A C33 H33C 109.5 . . ?
 H33B C33 H33C 109.5 . . ?
 O4 Zn2 O3 96.47(11) . . ?
 O4 Zn2 N5 153.37(11) . . ?
 O3 Zn2 N5 89.81(11) . . ?
 O4 Zn2 N6 87.49(12) . . ?
 O3 Zn2 N6 161.42(11) . . ?
 N5 Zn2 N6 79.02(12) . . ?
 O4 Zn2 N4 99.43(11) . . ?
 O3 Zn2 N4 95.45(11) . . ?
 N5 Zn2 N4 105.71(12) . . ?
 N6 Zn2 N4 101.82(12) . . ?
 C34 P2 C34 103.31(14) . 3_665 ?
 C34 P2 C34 103.31(14) . 2_655 ?
 C34 P2 C34 103.30(14) 3_665 2_655 ?
 C47 O3 Zn2 131.5(2) . . ?
 C58 O4 Zn2 130.1(2) . . ?
 C36 N4 C35 117.8(3) . . ?
 C36 N4 Zn2 121.1(3) . . ?
 C35 N4 Zn2 120.8(2) . . ?
 C45 N5 C39 121.4(3) . . ?
 C45 N5 Zn2 124.3(3) . . ?
 C39 N5 Zn2 114.2(2) . . ?
 C52 N6 C44 121.8(3) . . ?
 C52 N6 Zn2 124.1(3) . . ?
 C44 N6 Zn2 114.0(2) . . ?
 C35 C34 C38 117.1(3) . . ?
 C35 C34 P2 125.4(3) . . ?
 C38 C34 P2 117.3(3) . . ?
 N4 C35 C34 123.6(3) . . ?
 N4 C35 H35 118.2 . . ?
 C34 C35 H35 118.2 . . ?
 N4 C36 C37 122.7(4) . . ?
 N4 C36 H36 118.6 . . ?
 C37 C36 H36 118.6 . . ?
 C38 C37 C36 118.5(4) . . ?
 C38 C37 H37 120.7 . . ?

C36 C37 H37 120.7 . . ?
C37 C38 C34 120.2(4) . . ?
C37 C38 H38 119.9 . . ?
C34 C38 H38 119.9 . . ?
C40 C39 C44 118.8(4) . . ?
C40 C39 N5 124.4(4) . . ?
C44 C39 N5 116.7(3) . . ?
C41 C40 C39 120.5(4) . . ?
C41 C40 H40 119.8 . . ?
C39 C40 H40 119.8 . . ?
C42 C41 C40 120.4(4) . . ?
C42 C41 H41 119.8 . . ?
C40 C41 H41 119.8 . . ?
C43 C42 C41 120.2(4) . . ?
C43 C42 H42 119.9 . . ?
C41 C42 H42 119.9 . . ?
C42 C43 C44 120.7(4) . . ?
C42 C43 H43 119.6 . . ?
C44 C43 H43 119.6 . . ?
C43 C44 C39 119.3(4) . . ?
C43 C44 N6 125.3(4) . . ?
C39 C44 N6 115.3(3) . . ?
N5 C45 C46 127.1(4) . . ?
N5 C45 H45 116.4 . . ?
C46 C45 H45 116.4 . . ?
C51 C46 C47 120.0(4) . . ?
C51 C46 C45 115.5(3) . . ?
C47 C46 C45 124.4(4) . . ?
O3 C47 C46 122.6(4) . . ?
O3 C47 C48 119.0(3) . . ?
C46 C47 C48 118.4(4) . . ?
C49 C48 C47 117.8(4) . . ?
C49 C48 C59 122.0(4) . . ?
C47 C48 C59 120.2(4) . . ?
C48 C49 C50 124.0(4) . . ?
C48 C49 H49 118.0 . . ?
C50 C49 H49 118.0 . . ?
C51 C50 C49 118.4(4) . . ?
C51 C50 H50 120.8 . . ?
C49 C50 H50 120.8 . . ?
C50 C51 C46 121.4(4) . . ?
C50 C51 H51 119.3 . . ?
C46 C51 H51 119.3 . . ?
N6 C52 C53 126.3(4) . . ?
N6 C52 H52 116.8 . . ?
C53 C52 H52 116.8 . . ?
C54 C53 C58 120.3(4) . . ?
C54 C53 C52 115.8(4) . . ?
C58 C53 C52 123.8(4) . . ?
C55 C54 C53 119.8(5) . . ?
C55 C54 H54 120.1 . . ?
C53 C54 H54 120.1 . . ?
C54 C55 C56 120.0(5) . . ?
C54 C55 H55 120.0 . . ?

C56 C55 H55 120.0 . . ?
C57 C56 C55 123.3(4) . . ?
C57 C56 H56 118.4 . . ?
C55 C56 H56 118.4 . . ?
C56 C57 C58 117.8(4) . . ?
C56 C57 C63 122.5(4) . . ?
C58 C57 C63 119.6(4) . . ?
O4 C58 C53 122.4(3) . . ?
O4 C58 C57 118.8(4) . . ?
C53 C58 C57 118.7(4) . . ?
C61 C59 C48 111.5(4) . . ?
C61 C59 C62 107.1(4) . . ?
C48 C59 C62 110.1(3) . . ?
C61 C59 C60 108.4(4) . . ?
C48 C59 C60 109.4(3) . . ?
C62 C59 C60 110.3(4) . . ?
C59 C60 H60A 109.5 . . ?
C59 C60 H60B 109.5 . . ?
H60A C60 H60B 109.5 . . ?
C59 C60 H60C 109.5 . . ?
H60A C60 H60C 109.5 . . ?
H60B C60 H60C 109.5 . . ?
C59 C61 H61A 109.5 . . ?
C59 C61 H61B 109.5 . . ?
H61A C61 H61B 109.5 . . ?
C59 C61 H61C 109.5 . . ?
H61A C61 H61C 109.5 . . ?
H61B C61 H61C 109.5 . . ?
C59 C62 H62A 109.5 . . ?
C59 C62 H62B 109.5 . . ?
H62A C62 H62B 109.5 . . ?
C59 C62 H62C 109.5 . . ?
H62A C62 H62C 109.5 . . ?
H62B C62 H62C 109.5 . . ?
C66 C63 C64 106.7(4) . . ?
C66 C63 C65 110.4(4) . . ?
C64 C63 C65 108.1(4) . . ?
C66 C63 C57 110.4(4) . . ?
C64 C63 C57 111.4(4) . . ?
C65 C63 C57 109.7(4) . . ?
C63 C64 H64A 109.5 . . ?
C63 C64 H64B 109.5 . . ?
H64A C64 H64B 109.5 . . ?
C63 C64 H64C 109.5 . . ?
H64A C64 H64C 109.5 . . ?
H64B C64 H64C 109.5 . . ?
C63 C65 H65A 109.5 . . ?
C63 C65 H65B 109.5 . . ?
H65A C65 H65B 109.5 . . ?
C63 C65 H65C 109.5 . . ?
H65A C65 H65C 109.5 . . ?
H65B C65 H65C 109.5 . . ?
C63 C66 H66A 109.5 . . ?
C63 C66 H66B 109.5 . . ?

H66A C66 H66B 109.5 . . ?
C63 C66 H66C 109.5 . . ?
H66A C66 H66C 109.5 . . ?
H66B C66 H66C 109.5 . . ?

loop_
_geom_torsion_atom_site_label_1
_geom_torsion_atom_site_label_2
_geom_torsion_atom_site_label_3
_geom_torsion_atom_site_label_4
_geom_torsion
_geom_torsion_site_symmetry_1
_geom_torsion_site_symmetry_2
_geom_torsion_site_symmetry_3
_geom_torsion_site_symmetry_4
_geom_torsion_publ_flag
O2 Zn1 O1 C18 -170.1(4) ?
N3 Zn1 O1 C18 87.2(5) ?
N2 Zn1 O1 C18 26.0(4) ?
N1 Zn1 O1 C18 -68.5(4) ?
O1 Zn1 O2 C21 -154.3(3) ?
N3 Zn1 O2 C21 1.5(3) ?
N2 Zn1 O2 C21 -46.7(6) ?
N1 Zn1 O2 C21 101.0(3) ?
O1 Zn1 N1 C5 39.8(3) ?
O2 Zn1 N1 C5 138.4(3) ?
N3 Zn1 N1 C5 -130.1(3) ?
N2 Zn1 N1 C5 -50.6(3) ?
O1 Zn1 N1 C4 -149.0(3) ?
O2 Zn1 N1 C4 -50.5(3) ?
N3 Zn1 N1 C4 41.1(3) ?
N2 Zn1 N1 C4 120.5(3) ?
O1 Zn1 N2 C12 -14.6(3) ?
O2 Zn1 N2 C12 -123.2(5) ?
N3 Zn1 N2 C12 -172.6(4) ?
N1 Zn1 N2 C12 88.8(3) ?
O1 Zn1 N2 C6 169.2(3) ?
O2 Zn1 N2 C6 60.7(6) ?
N3 Zn1 N2 C6 11.2(3) ?
N1 Zn1 N2 C6 -87.4(3) ?
O1 Zn1 N3 C19 104.8(4) ?
O2 Zn1 N3 C19 0.9(3) ?
N2 Zn1 N3 C19 168.1(3) ?
N1 Zn1 N3 C19 -99.1(3) ?
O1 Zn1 N3 C7 -74.8(4) ?
O2 Zn1 N3 C7 -178.8(3) ?
N2 Zn1 N3 C7 -11.6(3) ?
N1 Zn1 N3 C7 81.3(3) ?
C1 P1 C1 C2 -4.0(4) 2 . . . ?
C1 P1 C1 C2 99.2(3) 3 . . . ?
C1 P1 C1 C5 176.0(3) 2 . . . ?
C1 P1 C1 C5 -80.9(4) 3 . . . ?
C5 C1 C2 C3 0.3(6) ?
P1 C1 C2 C3 -179.7(3) ?

C1 C2 C3 C4 1.3(6) ?
 C5 N1 C4 C3 1.1(6) ?
 Zn1 N1 C4 C3 -170.4(3) ?
 C2 C3 C4 N1 -2.1(6) ?
 C4 N1 C5 C1 0.6(6) ?
 Zn1 N1 C5 C1 171.9(3) ?
 C2 C1 C5 N1 -1.3(6) ?
 P1 C1 C5 N1 178.7(3) ?
 C12 N2 C6 C11 -6.1(6) ?
 Zn1 N2 C6 C11 170.1(3) ?
 C12 N2 C6 C7 174.5(4) ?
 Zn1 N2 C6 C7 -9.3(4) ?
 C11 C6 C7 C8 -0.3(6) ?
 N2 C6 C7 C8 179.2(3) ?
 C11 C6 C7 N3 -180.0(3) ?
 N2 C6 C7 N3 -0.5(5) ?
 C19 N3 C7 C8 10.9(6) ?
 Zn1 N3 C7 C8 -169.4(3) ?
 C19 N3 C7 C6 -169.4(4) ?
 Zn1 N3 C7 C6 10.2(4) ?
 C6 C7 C8 C9 1.5(6) ?
 N3 C7 C8 C9 -178.8(4) ?
 C7 C8 C9 C10 -1.3(6) ?
 C8 C9 C10 C11 -0.2(6) ?
 C9 C10 C11 C6 1.4(7) ?
 C7 C6 C11 C10 -1.2(6) ?
 N2 C6 C11 C10 179.4(4) ?
 C6 N2 C12 C13 178.4(4) ?
 Zn1 N2 C12 C13 2.6(6) ?
 N2 C12 C13 C14 -172.0(4) ?
 N2 C12 C13 C18 7.5(7) ?
 C18 C13 C14 C15 -1.2(8) ?
 C12 C13 C14 C15 178.3(5) ?
 C13 C14 C15 C16 0.1(9) ?
 C14 C15 C16 C17 1.4(9) ?
 C15 C16 C17 C18 -1.7(8) ?
 C15 C16 C17 C26 179.6(6) ?
 Zn1 O1 C18 C13 -24.3(6) ?
 Zn1 O1 C18 C17 157.4(3) ?
 C14 C13 C18 O1 -177.4(4) ?
 C12 C13 C18 O1 3.1(7) ?
 C14 C13 C18 C17 0.9(7) ?
 C12 C13 C18 C17 -178.6(4) ?
 C16 C17 C18 O1 178.9(4) ?
 C26 C17 C18 O1 -2.4(7) ?
 C16 C17 C18 C13 0.5(7) ?
 C26 C17 C18 C13 179.2(5) ?
 C7 N3 C19 C20 179.1(4) ?
 Zn1 N3 C19 C20 -0.5(6) ?
 N3 C19 C20 C25 -178.5(4) ?
 N3 C19 C20 C21 -2.2(7) ?
 Zn1 O2 C21 C20 -4.2(6) ?
 Zn1 O2 C21 C22 175.2(3) ?
 C25 C20 C21 O2 -179.3(4) ?

C19 C20 C21 O2 4.5(6) ?
 C25 C20 C21 C22 1.3(6) ?
 C19 C20 C21 C22 -174.9(4) ?
 O2 C21 C22 C23 179.4(4) ?
 C20 C21 C22 C23 -1.2(6) ?
 O2 C21 C22 C30 -1.4(6) ?
 C20 C21 C22 C30 178.0(3) ?
 C21 C22 C23 C24 0.1(7) ?
 C30 C22 C23 C24 -179.1(4) ?
 C22 C23 C24 C25 1.0(7) ?
 C23 C24 C25 C20 -0.9(7) ?
 C21 C20 C25 C24 -0.2(7) ?
 C19 C20 C25 C24 176.3(4) ?
 C16 C17 C26 C27 -119.4(5) ?
 C18 C17 C26 C27 61.9(6) ?
 C16 C17 C26 C29 0.7(8) ?
 C18 C17 C26 C29 -177.9(5) ?
 C16 C17 C26 C28 118.5(5) ?
 C18 C17 C26 C28 -60.2(6) ?
 C23 C22 C30 C33 -119.9(5) ?
 C21 C22 C30 C33 60.9(5) ?
 C23 C22 C30 C31 0.3(6) ?
 C21 C22 C30 C31 -179.0(4) ?
 C23 C22 C30 C32 120.2(5) ?
 C21 C22 C30 C32 -59.1(5) ?
 O4 Zn2 O3 C47 158.5(3) ?
 N5 Zn2 O3 C47 4.4(3) ?
 N6 Zn2 O3 C47 57.0(5) ?
 N4 Zn2 O3 C47 -101.3(3) ?
 O3 Zn2 O4 C58 171.9(3) ?
 N5 Zn2 O4 C58 -85.5(4) ?
 N6 Zn2 O4 C58 -26.4(3) ?
 N4 Zn2 O4 C58 75.2(3) ?
 O4 Zn2 N4 C36 -27.5(3) ?
 O3 Zn2 N4 C36 -125.0(3) ?
 N5 Zn2 N4 C36 143.6(3) ?
 N6 Zn2 N4 C36 61.9(3) ?
 O4 Zn2 N4 C35 145.6(3) ?
 O3 Zn2 N4 C35 48.1(3) ?
 N5 Zn2 N4 C35 -43.2(3) ?
 N6 Zn2 N4 C35 -125.0(3) ?
 O4 Zn2 N5 C45 -109.1(3) ?
 O3 Zn2 N5 C45 -4.9(3) ?
 N6 Zn2 N5 C45 -170.0(3) ?
 N4 Zn2 N5 C45 90.7(3) ?
 O4 Zn2 N5 C39 67.1(4) ?
 O3 Zn2 N5 C39 171.3(2) ?
 N6 Zn2 N5 C39 6.2(2) ?
 N4 Zn2 N5 C39 -93.1(2) ?
 O4 Zn2 N6 C52 20.1(3) ?
 O3 Zn2 N6 C52 123.0(4) ?
 N5 Zn2 N6 C52 177.0(3) ?
 N4 Zn2 N6 C52 -79.1(3) ?
 O4 Zn2 N6 C44 -164.2(2) ?

O3 Zn2 N6 C44 -61.2(5) ?
N5 Zn2 N6 C44 -7.2(2) ?
N4 Zn2 N6 C44 96.7(2) ?
C34 P2 C34 C35 102.4(2) 3_665 . . . ?
C34 P2 C34 C35 -4.9(4) 2_655 . . . ?
C34 P2 C34 C38 -84.0(4) 3_665 . . . ?
C34 P2 C34 C38 168.6(3) 2_655 . . . ?
C36 N4 C35 C34 0.1(5) ?
Zn2 N4 C35 C34 -173.2(3) ?
C38 C34 C35 N4 -0.7(5) ?
P2 C34 C35 N4 172.9(3) ?
C35 N4 C36 C37 0.8(6) ?
Zn2 N4 C36 C37 174.1(3) ?
N4 C36 C37 C38 -1.1(6) ?
C36 C37 C38 C34 0.5(6) ?
C35 C34 C38 C37 0.4(6) ?
P2 C34 C38 C37 -173.8(3) ?
C45 N5 C39 C40 -6.5(5) ?
Zn2 N5 C39 C40 177.2(3) ?
C45 N5 C39 C44 171.9(3) ?
Zn2 N5 C39 C44 -4.4(4) ?
C44 C39 C40 C41 -0.4(6) ?
N5 C39 C40 C41 178.0(3) ?
C39 C40 C41 C42 1.0(6) ?
C40 C41 C42 C43 -0.9(6) ?
C41 C42 C43 C44 0.0(6) ?
C42 C43 C44 C39 0.6(6) ?
C42 C43 C44 N6 -176.1(4) ?
C40 C39 C44 C43 -0.5(5) ?
N5 C39 C44 C43 -179.0(3) ?
C40 C39 C44 N6 176.6(3) ?
N5 C39 C44 N6 -1.9(5) ?
C52 N6 C44 C43 -0.1(6) ?
Zn2 N6 C44 C43 -176.0(3) ?
C52 N6 C44 C39 -177.0(4) ?
Zn2 N6 C44 C39 7.1(4) ?
C39 N5 C45 C46 -174.3(3) ?
Zn2 N5 C45 C46 1.6(5) ?
N5 C45 C46 C51 -179.9(4) ?
N5 C45 C46 C47 4.8(6) ?
Zn2 O3 C47 C46 -0.2(5) ?
Zn2 O3 C47 C48 -178.6(3) ?
C51 C46 C47 O3 179.2(3) ?
C45 C46 C47 O3 -5.6(6) ?
C51 C46 C47 C48 -2.3(5) ?
C45 C46 C47 C48 172.8(3) ?
O3 C47 C48 C49 179.9(4) ?
C46 C47 C48 C49 1.4(5) ?
O3 C47 C48 C59 -0.5(6) ?
C46 C47 C48 C59 -179.0(4) ?
C47 C48 C49 C50 0.4(6) ?
C59 C48 C49 C50 -179.3(4) ?
C48 C49 C50 C51 -1.2(7) ?
C49 C50 C51 C46 0.3(6) ?

C47 C46 C51 C50 1.5(6) ?
 C45 C46 C51 C50 -174.1(4) ?
 C44 N6 C52 C53 175.8(4) ?
 Zn2 N6 C52 C53 -8.7(6) ?
 N6 C52 C53 C54 174.8(4) ?
 N6 C52 C53 C58 -7.5(7) ?
 C58 C53 C54 C55 0.3(7) ?
 C52 C53 C54 C55 178.1(5) ?
 C53 C54 C55 C56 -1.4(8) ?
 C54 C55 C56 C57 1.7(9) ?
 C55 C56 C57 C58 -0.9(8) ?
 C55 C56 C57 C63 177.2(5) ?
 Zn2 O4 C58 C53 19.7(6) ?
 Zn2 O4 C58 C57 -160.2(3) ?
 C54 C53 C58 O4 -179.5(4) ?
 C52 C53 C58 O4 3.0(6) ?
 C54 C53 C58 C57 0.5(6) ?
 C52 C53 C58 C57 -177.1(4) ?
 C56 C57 C58 O4 179.8(4) ?
 C63 C57 C58 O4 1.6(6) ?
 C56 C57 C58 C53 -0.2(6) ?
 C63 C57 C58 C53 -178.3(4) ?
 C49 C48 C59 C61 -1.8(6) ?
 C47 C48 C59 C61 178.6(4) ?
 C49 C48 C59 C62 -120.5(4) ?
 C47 C48 C59 C62 59.9(5) ?
 C49 C48 C59 C60 118.1(4) ?
 C47 C48 C59 C60 -61.5(5) ?
 C56 C57 C63 C66 122.3(5) ?
 C58 C57 C63 C66 -59.6(5) ?
 C56 C57 C63 C64 3.9(6) ?
 C58 C57 C63 C64 -178.0(4) ?
 C56 C57 C63 C65 -115.8(5) ?
 C58 C57 C63 C65 62.3(5) ?

_diffn_measured_fraction_theta_max 1.000
 _diffn_reflns_theta_full 22.48
 _diffn_measured_fraction_theta_full 1.000
 _refine_diff_density_max 0.387
 _refine_diff_density_min -0.394
 _refine_diff_density_rms 0.065

loop_
 _platon_squeeze_void_nr
 _platon_squeeze_void_average_x
 _platon_squeeze_void_average_y
 _platon_squeeze_void_average_z
 _platon_squeeze_void_volume
 _platon_squeeze_void_count_electrons
 1 0.000 1.000 0.250 1354.2 143.9
 2 0.000 0.000 0.750 1354.4 144.6
 3 0.333 0.667 0.104 342.1 51.5
 4 0.333 0.667 0.604 342.1 51.2
 5 0.333 0.667 0.358 31.5 2.2

6 0.333 0.667 0.858 31.5 2.2
7 0.667 0.333 0.396 342.1 50.1
8 0.667 0.333 0.896 342.0 49.9
9 0.667 0.333 0.142 31.5 3.0
10 0.667 0.333 0.642 31.5 3.2
_platon_squeeze_details
; ?
;