UvA-DARE (Digital Academic Repository)

A versatile synthesis route for metal@SiO₂ core-shell nanoparticles using 11-mercaptoundecanoic acid as primer

Zhang, Y.; Kong, X.; Xue, B.; Zeng, Q.; Liu, X.; Tu, L.; Liu, K.; Zhang, H.

DOI

[10.1039/c3tc31171f](https://doi.org/10.1039/c3tc31171f)

Publication date

2013

Document Version

Other version

Published in

Journal of Materials Chemistry. C

[Link to publication](#)

Citation for published version (APA):

Zhang, Y., Kong, X., Xue, B., Zeng, Q., Liu, X., Tu, L., Liu, K., & Zhang, H. (2013). A versatile synthesis route for metal@SiO₂ core-shell nanoparticles using 11-mercaptoundecanoic acid as primer. *Journal of Materials Chemistry. C*, 1(39), 6355-6363.
<https://doi.org/10.1039/c3tc31171f>

General rights

It is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), other than for strictly personal, individual use, unless the work is under an open content license (like Creative Commons).

Disclaimer/Complaints regulations

If you believe that digital publication of certain material infringes any of your rights or (privacy) interests, please let the Library know, stating your reasons. In case of a legitimate complaint, the Library will make the material inaccessible and/or remove it from the website. Please Ask the Library: <https://uba.uva.nl/en/contact>, or a letter to: Library of the University of Amsterdam, Secretariat, Singel 425, 1012 WP Amsterdam, The Netherlands. You will be contacted as soon as possible.

UvA-DARE is a service provided by the library of the University of Amsterdam (<https://dare.uva.nl>)

A Versatile Synthesis Route for Metal@SiO₂ Core-Shell Nanoparticles Using 11-mercaptoundecanoic Acid as Primer

Youlin Zhang^{a,c}, Xianggui Kong^{a*}, Bin Xue^{a,b}, Qinghui Zeng^a, Xiaomin Liu^a, Langping Tu^{a,b}, Kai Liu^c, Hong Zhang^{c*}

Supplementary information

Figure S1. UV-vis spectra of citrate-stabilized Au NP and MUA modified Au NPs.

Figure S2. FE-SEM images for the SiO₂-coated thiol-modified Au NPs: a. MPA-modified Au NPs, b. MHA-modified Au NPs

To demonstrate whether MPA ($\text{SH}-(\text{CH}_2)_2-\text{COOH}$) or MHA ($\text{SH}-(\text{CH}_2)_{15}-\text{COOH}$) could also be used as linker molecules, therefore, the same method was used to modify the citrate-stabilized Au nanoparticles by using 3-mercaptopropionic acid (MPA) or 16-mercaptohexadecanoic acid (MHA) to replace the MUA. Figure S2 shows FE-SEM images for the SiO_2 -coated thiol-modified Au NPs produced by this approach. In the case of the Au NPs modified with $\text{SH}-(\text{CH}_2)_n-\text{COOH}$ ($n=2$), the Au NPs form inhomogeneous silica shell and free-gold Au NPs (see Figure S2A). However, for the Au NPs stabilized with $\text{SH}-(\text{CH}_2)_n-\text{COOH}$ ($n=15$), mostly single gold colloids coated with a silica shell were dominated (see Figure S2B).

As is well known, the concentration of ammonium hydroxide and the ethanol to water ratio played important roles in controlling the deposition of silica on the Au NPs. In the work, we examined the effects of the concentrations of ammonium hydroxide and the ethanol to water ratio on the encapsulation of silica. It turned out that homogeneous homogeneous silica-coated Au NPs could not be obtained in this way. Apparently, these results indicated that the affinity of carboxyl to silica for $\text{SH}-(\text{CH}_2)_n-\text{COOH}$ ($n=2, 10$ or 15) ligand was also related with 'n'. The above results obtained for the different thiol compounds showed that the silica was directly growing onto the chemical-adsorbed thiol compounds ($-\text{COOH}$).

Figure S3. Influence of silica shell thickness on UV-vis spectra of Au NPs encapsulated in silica shell.

Figure S4. SEM of silica-coated Au NRs produced by varying the amounts of the TEOS for A-B. The shell thicknesses were 50 nm (A) and 30 nm (B). The scale bar was 60 nm.

Figure S5. UV-visible spectra of Au NRs colloids before (black) and after silica coating (red). The spectra were normalized at the longitudinal band maximum

Figure S6. UV-vis spectra of citrate-stabilized Ag NP and MUA modified Ag NPs.

Figure S7. Influence of silica shell thickness on UV-vis spectra of Ag NPs (20 nm in diameter) encapsulated in silica shell.

Figure S8. Distance dependent fluorescent enhancement factor of FITC by Ag and Au NPs.