UvA-DARE (Digital Academic Repository)

Supramolecular encapsulation of C60 in a water-soluble calixarene - a core-shell charge-transfer complex

Williams, R.M.; Verhoeven, J.W.

Publication date
1992

Published in
Recueil des travaux chimiques des Pays-Bas = Journal of the Royal Netherlands Chemical Society

[Link to publication](#)

Citation for published version (APA):

Williams, R. M., & Verhoeven, J. W. (1992). Supramolecular encapsulation of C60 in a water-soluble calixarene - a core-shell charge-transfer complex. *Recueil des travaux chimiques des Pays-Bas = Journal of the Royal Netherlands Chemical Society*, 111(12), 531-532.

General rights

It is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), other than for strictly personal, individual use, unless the work is under an open content license (like Creative Commons).

Disclaimer/Complaints regulations

If you believe that digital publication of certain material infringes any of your rights or (privacy) interests, please let the Library know, stating your reasons. In case of a legitimate complaint, the Library will make the material inaccessible and/or remove it from the website. Please Ask the Library: <https://uba.uva.nl/en/contact>, or a letter to: Library of the University of Amsterdam, Secretariat, Singel 425, 1012 WP Amsterdam, The Netherlands. You will be contacted as soon as possible.

UvA-DARE is a service provided by the library of the University of Amsterdam (<https://dare.uva.nl>)

Supramolecular Encapsulation of C_{60} in a Water Soluble Calixarene; A Core-Shell Charge Transfer Complex.

René M. Williams and Jan W. Verhoeven*

Laboratory of Organic Chemistry, University of Amsterdam,
Nieuwe Achtergracht 129, 1018 WS Amsterdam, The Netherlands
(Received November 12, 1992)

Abstract. A calix[8]arene derivative has been found to form a water soluble complex with fullerene- C_{60} , but not with C_{70} , which allows extraction of C_{60} from e.g. toluene into the aqueous phase. Charge transfer character of the complex is evident from strong charge transfer absorption around 440 nm measured in water. Molecular modeling calculations indicate a core-shell structure for the complex.

Introduction

Functionalising fullerenes^{1,2,3} by using them as non-covalently bound building blocks in supramolecular constructs, leaving their extensive π -systems and remarkable redox properties essentially unimpaired, is a great challenge. Thus much effort is being directed to the construction of endohedral systems in which the nonpolar carbon-"shell" of the fullerenes encapsulates a smaller "core"-atom or perhaps even a molecule. We now report, however, a supramolecular system in which C_{60} itself acts as a "core" embedded in the "shell" of a functionalised, water soluble calixarene leading to extensive electronic interaction of the charge transfer (CT) type between the π -systems of core and shell⁴.

Results and discussion

The electron deficient nature of the fullerenes C_{60} and C_{70} allows these to form CT-complexes with π -electron donors of the aniline type⁵⁻⁸. It has also been reported^{4c} that whereas solutions of C_{60} in solvents such as benzene and toluene are

purple, its solution in the neat 1,2-dimethoxybenzene (veratrole) are deep yellow. We now observed that solutions of C_{60} in liquid, π -donating methoxy-substituted benzenes vary from light yellow via deep yellow to orange upon increasing substitution (mono-, 1,2-di- and 1,2,4 tri-MeO) and that the solubility of C_{60} in such media appears to be enhanced. Comparison of the spectra of C_{60} in toluene and in veratrole (see Fig. 1) revealed that in the latter a broad CT-absorption is readily detectable as a shoulder around 450 nm. (Note that the spectra in Figure 1 have been normalised on the strong 333-340 nm band, $\epsilon = 51286 \text{ l.mol}^{-1}.\text{cm}^{-1}$ in toluene^{9,10}). The apparent extinction coefficient of the CT-absorption at 450 nm amounts to $\epsilon = 5000$. This compares to $\epsilon = 3700$ (600 nm) for the N,N-diethylaniline complex⁷ and $\epsilon = 10200$ (624 nm) for the N,N-dimethylaniline complex⁸, derived from Benesi-Hildebrand type analysis.

As the alkoxybenzene unit forms a basic building-block of many calixarene host-molecules, we decided to investigate the possibility to encapsulate C_{60} in a water-soluble calixarene of suitable dimensions.

Molecular mechanics simulation via the Tripos Force Field¹¹ using Gasteiger-Hückel charges, indicated that from the available calixarenes especially calix[8]arene should be a suitable host for C_{60} . Fig. 2 shows the predicted structure for such a complex involving the water soluble calix[8]aryloxy-49, 50, 51, 52, 53, 54, 55, 56 octakis-(propane-3-sulphonate) (1). Synthesis of 1 was achieved by reaction of calix[8]arene (Janssen Chimica) with 1,3-propanesultone, following literature procedures¹².

1

In a typical solubilisation experiment 1 mg pure powdered C_{60} was added to a colorless solution of 40 mg 1 in 10 ml of demineralized water and this mixture was refluxed. Dissolution was evident from yellowing of the mixture. Interestingly no solubilisation of C_{70} occurs under these conditions. After 32

Fig. 1: Electronic absorption spectra of C_{60} in neat toluene, in neat veratrole and solubilized in water by 1.

Fig.2: 'Top' and 'side' view of the 1- C_{60} complex obtained by molecular modeling.

hours solid particles were removed by centrifugation and filtration resulting in a clear yellow solution. C_{60} cannot be extracted from this solution with either carbon disulfide or toluene. In fact, refluxing a solution of C_{60} in toluene with a solution of 1 in water allows one to extract C_{60} into the aqueous phase. At the other hand C_{60} can be extracted unchanged with toluene from the solid residue which remains after full evaporation of the aqueous solution. Together with the electronic absorption data (see, below) these experiments indicate that both hydrophobic interaction and CT-interaction play a role in the complex formation.

The absorption spectrum of the yellow aqueous solution of the complex between 1 and C_{60} displays absorption maxima at 340, 440, 620 and 680 (sh) nm (see Fig. 1). From comparison with the spectra of C_{60} in toluene and in veratrole the broad 440 nm band is attributed to a CT transition in which electron transfer from the calixarene shell to the fullerene core takes place. The extinction coefficient at 440 nm is ca. 15000 which indicates enhanced electronic interaction as compared to the intermolecular complexes of C_{60} with simple aromatic electron donors (see above)¹³. A stronger electronic interaction is also indicated by the shift (336→340 nm) and broadening of the strong local C_{60} absorption and an apparent intensification of its weak long wavelength absorption in the 600-700 nm region (see inset of Fig. 1). The latter effect may tentatively be attributed⁸ to a lowering of the local symmetry by complexation that reduces the forbidden character of these weak transitions compared to "isolated" C_{60} .

The molecular mechanics calculations (see Fig. 2) support the occurrence of strong π - π overlap. Interestingly the complexed calixarene is predicted not to have a full cone conformation. Starting optimization of the complex with 1 in a cone conformation results in a structure for the complex with three aryl rings bending out of the cone (a sort of half cone/alternate cone conformation). While this sacrifices interaction with three aryl-rings of the calixarene it allows for optimal π - π interaction of the other five rings with the fullerene.

It will clearly be of great interest to secure further the configuration of the present complex as well as to further explore the selectivity of 1 and related calixarenes in encapsulating various fullerenes. The water solubility and the Acceptor-core/ Donor-shell structure of such complexes open new possibilities to employ the strong photo-oxidative properties of the fullerene core in electron abstraction from reductants in aqueous media eventually mediated by the shell upon excitation in the CT absorption band. In this context the

present complex provides an interesting vehicle for transport of the hydrophobic fullerene unit via the aqueous phase which may allow its incorporation in bio-redox systems. These possibilities are presently under active investigation.

Acknowledgement

We thank H.J. Verhey and R.D. Mout for their help with the molecular modeling calculations, the results of which were expertly visualised by Dr. A.M. Brouwer using the facilities of the SARA Visualisation Centre.

This research was supported by the Netherlands Foundation for Chemical Research (SON) with financial aid from the Netherlands Organization for the Advancement of Scientific Research (NWO).

References and notes

- 1) For a recent review of fullerene functionalisation: H. Schwarz, *Angew. Chem. Int. Ed. Engl.* **3**, 293 (1992).
- 2) H.W. Kroto, J.R. Heath, S.C. O'Brien, R.F. Curl, and R.E. Smalley, *Nature* **318**, 162 (1985).
- 3) W. Krätschmer, L.B. Lamb, K. Fostiropoulos, and D.R. Huffman, *Nature* **347**, 354 (1990).
- 4a) Such interaction is absent the water soluble complex of C_{60} and γ -cyclodextrin reported by Andersson et al.^{4b}, but interestingly a solid inclusion compound of the CT type of C_{60} in hydroquinone has been reported by Ermer^{4c}.
- 4b) T. Andersson, K. Nilsson, M. Sundahl, G. Westman, and O. Wennerström, *J. Chem. Soc., Chem. Commun.* 604 (1992).
- 4c) O. Ermer, *Helv. Chim. Acta* **74**, 1339 (1991).
- 5) J.W. Verhoeven, T. Scherer, and D. Heymann, *Recl. Trav. Chim. Pays-Bas* **110**, 349 (1991).
- 6) R.M. Williams, and J.W. Verhoeven, *Chem. Phys. Lett.* **194**, 446 (1992).
- 7) Y. Wang, and L-T. Cheng, *J. Phys. Chem.* **96**, 1530 (1992).
- 8) R.J. Sension, A.Z. Szarka, G.R. Smith, and R.M. Hochstrasser, *Chem. Phys. Lett.* **185**, 179 (1991).
- 9) J.P. Hare, H.W. Kroto, and R. Taylor, *Chem. Phys. Lett.* **177**, 394 (1991).
- 10) P.M. Allemand, A. Koch, F. Wudl, Y. Rubin, F. Diederich, M.M. Alvarez, S.J. Anz, and R.L. Whetten, *J. Am. Chem. Soc.* **113**, 1050 (1991).
- 11) Sybyl 5.32, Tripos Associates, Inc., 1699 South Hanley Road, Suite 303, St. Louis, Missouri 63144, USA.
- 12) S. Shinkai, T. Arimura, K. Araki, and H. Kawabata, *J. Chem. Soc. Perkin Trans. I* 2039 (1989).
- 13) Based on this extinction a maximum achievable concentration of the 1- C_{60} complex in water at 25°C is $0.5 \cdot 10^{-4}$ M.