UvA-DARE (Digital Academic Repository)

Highly selective adsorption of ethylene over ethane in a MOF featuring the combination of open metal site and π -complexation

Zhang, Y.; Li, B.; Krishna, R.; Wu, Z.; Ma, D.; Shi, Z.; Pham, T.; Forrest, K.; Space, B.; Ma, S.

DOI

[10.1039/c4cc09774b](https://doi.org/10.1039/c4cc09774b)

Publication date

2015

Document Version

Final published version

Published in

Chemical Communications

[Link to publication](#)

Citation for published version (APA):

Zhang, Y., Li, B., Krishna, R., Wu, Z., Ma, D., Shi, Z., Pham, T., Forrest, K., Space, B., & Ma, S. (2015). Highly selective adsorption of ethylene over ethane in a MOF featuring the combination of open metal site and π -complexation. *Chemical Communications*, 51(13), 2714-2717. <https://doi.org/10.1039/c4cc09774b>

General rights

It is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), other than for strictly personal, individual use, unless the work is under an open content license (like Creative Commons).

Disclaimer/Complaints regulations

If you believe that digital publication of certain material infringes any of your rights or (privacy) interests, please let the Library know, stating your reasons. In case of a legitimate complaint, the Library will make the material inaccessible and/or remove it from the website. Please Ask the Library: <https://uba.uva.nl/en/contact>, or a letter to: Library of the University of Amsterdam, Secretariat, Singel 425, 1012 WP Amsterdam, The Netherlands. You will be contacted as soon as possible.

UvA-DARE is a service provided by the library of the University of Amsterdam (<https://dare.uva.nl>)

Cite this: *Chem. Commun.*, 2015, 51, 2714

Received 6th December 2014,
Accepted 3rd January 2015

DOI: 10.1039/c4cc09774b

www.rsc.org/chemcomm

Highly selective adsorption of ethylene over ethane in a MOF featuring the combination of open metal site and π -complexation†

Yiming Zhang,^a Baiyan Li,^{*ab} Rajamani Krishna,^c Zili Wu,^d Dingxuan Ma,^b Zhan Shi,^b Tony Pham,^a Katherine Forrest,^a Brian Space^a and Shengqian Ma^{*a}

The introduction of the combination of open metal site (OMS) and π -complexation into MOF has led to very high ethylene–ethane adsorption selectivity at 318 K, as illustrated in the context of MIL-101–Cr–SO₃Ag. The interactions with ethylene from both OMS and π -complexation in MIL-101–Cr–SO₃Ag have been investigated by *in situ* IR spectroscopic studies and computational calculations, which suggest that π -complexation contributes dominantly to the high ethylene–ethane adsorption selectivity.

The separation of ethylene–ethane mixtures represents an important industrial process, and is also considered as one of the most challenging chemical separations in the large scale because of the similar molecular sizes and volatilities between ethylene and ethane.¹ The current technology in industry is dictated by cryogenic distillation, which is cost and energy intensive due to the requirement of high pressure and low temperature.² Among several alternative approaches^{3,4} under development for energy-efficient ethylene–ethane separation at higher temperatures (at or above room temperature), adsorptive separation using porous solid materials has attracted particular attention.⁵

Due to their high surface areas, tunable pore sizes, and functionalizable pore surfaces as well as the amenability of design and modular nature, metal–organic frameworks (MOFs)⁶ have been recently explored as a new type of porous solid materials for hydrocarbon separation,⁷ including the separation

of ethylene–ethane mixtures.⁸ Extensive efforts have been devoted to the creation of open metal sites (OMSs) in MOFs to enhance the selectivity of ethylene over ethane, due to the stronger interactions of ethylene with OMSs compared with ethane.^{8a} Recently, we demonstrated that a Ag(I) ion functionalized porous aromatic framework (PAF) exhibited exceptional ethylene–ethane adsorption selectivity as a result of the formation of π -complexation between ethylene molecules and Ag(I) ions.⁹ We speculate that if such a kind of π -complexation can be coupled with OMSs into MOFs, the adsorption selectivity of ethylene over ethane can be further enhanced in MOFs because of the strong interactions with ethylene from both π -complexation and OMSs. In this contribution, we report the introduction of the combination of OMSs and π -complexation into MOF for the first time, as exemplified in the context of MIL-101–Cr–SO₃Ag, which demonstrates exceptional ethylene–ethane adsorption selectivity at 318 K, surpassing benchmark porous solid materials of zeolites, MOFs and PAFs. The interactions with ethylene from both OMSs and π -complexation have been investigated using *in situ* IR spectroscopic studies and computational calculations.

MIL-101–Cr–SO₃Ag was afforded *via* Ag(I) ion exchange of the sulphonic acid functionalized MIL-101–Cr (MIL-101–Cr–SO₃H), which was prepared using the method reported in the literature¹⁰ (Scheme 1). The powder X-ray diffraction studies show that the patterns of MIL-101–Cr–SO₃Ag are consistent with those of MIL-101–Cr–SO₃H (Fig. S1, ESI†), indicating the maintenance of structural integrity during the Ag(I) exchange process. N₂ gas sorption isotherms collected at 77 K (Fig. S2, ESI†) reveal Brunauer–Emmett–Teller (BET) surface areas of 1570 m² g^{−1} and 1374 m² g^{−1} for MIL-101–Cr–SO₃H and MIL-101–Cr–SO₃Ag, respectively. The decreasing surface area should be presumably due to the introduction of Ag(I) ions. The presence of Ag(I) in MIL-101–Cr–SO₃Ag was confirmed using X-ray photoelectron spectroscopy (XPS) analysis, which shows the silver signals at a binding energy of 368.8 eV and 374.8 eV (Fig. S3, ESI†) corresponding to the peaks of Ag3d_{5/2} and Ag3d_{3/2}, respectively. Inductively coupled plasma mass spectrometry (ICP-MS) suggests that ~51% SO₃H were exchanged into SO₃Ag.

^a Department of Chemistry, University of South Florida, 4202 E. Fowler Avenue, Tampa, FL 33620, USA. E-mail: sqma@usf.edu, libaiyan@gmail.com; Fax: +1-813-974-3203; Tel: +1-813-974-5217

^b State Key Laboratory of Inorganic Synthesis and Preparative Chemistry, College of Chemistry, Jilin University, Changchun 130012, People's Republic of China

^c Van't Hoff Institute for Molecular Sciences, University of Amsterdam, Science Park 904, 1098 XH Amsterdam, Netherlands

^d Center for Nanophase Materials Science and Chemical Science Division, Oak Ridge National Laboratory, TN 37831, USA

† Electronic supplementary information (ESI) available: Detailed methods for catalyst preparation, measurements, analysis and catalytic process. See DOI: 10.1039/c4cc09774b

Scheme 1 Schematic illustration of Ag(I) exchange in MIL-101-Cr-SO₃H to afford MIL-101-Cr-SO₃Ag.

The low-pressure ethylene–ethane sorption isotherms were collected at 296 K and 318 K. Compared with the pristine MIL-101-Cr-SO₃H, the introduction of Ag(I) ion into MIL-101-Cr-SO₃H results in a significant enhancement of ethylene adsorption capacity despite the decrease in surface area. Under 1 atm pressure, the ethylene uptake amounts increase from 42 cm³ g^{−1} at 296 K and 37 cm³ g^{−1} at 318 K for MIL-101-Cr-SO₃H to 73 cm³ g^{−1} at 296 K and 63 cm³ g^{−1} at 318 K for MIL-101-Cr-SO₃Ag (Fig. 1). Interestingly, in contrast to the ethylene adsorption, the uptake amounts of ethane at 296 K and 318 K for two samples are comparable (Fig. S4 and S5, ESI[†]), suggesting that the introduction of Ag(I) ions would not increase the ethane uptake capacity.

Ethylene–ethane adsorption selectivities were calculated using ideal adsorbed solution theory (IAST)¹¹ for MIL-101-Cr-SO₃H and MIL-101-Cr-SO₃Ag (Fig. 2). For an equimolar mixture of ethylene and ethane at 318 K, the adsorption selectivity (S_{ads}) obtained for MIL-101-Cr-SO₃Ag is 9.7 at 100 kPa, far exceeding that calculated for MIL-101-Cr-SO₃H ($S_{\text{ads}} = 1.2$). This result suggests the predominant contribution from Ag(I) ion in comparison with the OMS of Cr(III) to the enhancement of ethylene–ethane adsorption selectivity. The ethylene–ethane adsorption selectivity of MIL-101-Cr-SO₃Ag at 318 K and 100 kPa is also significantly higher than those of the zeolite NaX,^{8b} the MOFs^{8b} CoMOF-74 [also known as (a.k.a.) Co₂(dobdc)], MgMOF-74 [a.k.a. Mg₂(dobdc)], CuBTC (a.k.a. HKUST-1) (Fig. 2), exhibiting ethylene–ethane selectivities of 6.8, 5.7, 4.7, and 3.8, respectively. It slightly surpasses the best

Fig. 1 C₂H₄ sorption isotherms of MIL-101-Cr-SO₃Ag (black: 296 K; red: 318 K) and MIL-101-Cr-SO₃H (green: 296 K; blue 318 K). Filled: adsorption; unfilled: desorption.

Fig. 2 Comparison of the IAST calculations for C₂H₄–C₂H₆ adsorption selectivities for MIL-101-Cr-SO₃Ag with MIL-101-Cr-SO₃H and other porous materials¹⁰ at 318 K.

performance MOF of FeMOF-74 (a.k.a. Fe₂(dobdc)) ($S_{\text{ads}} = 8.9$) and PAF of PAF-1-SO₃Ag⁹ ($S_{\text{ads}} = 6.9$). It is worth noting that the higher ethylene–ethane adsorption selectivities of MIL-101-Cr-SO₃Ag compared to PAF-1-SO₃Ag indicate the possible cooperative contribution from the OMS of Cr(III) to further boosting the ethylene–ethane adsorption selectivities for MIL-101-Cr-SO₃Ag.

To provide a better understanding of the exceptional ethylene adsorption properties of MIL-101-Cr-SO₃Ag, the isosteric heats of adsorption (Q_{st}) were calculated using the Clausius–Clapeyron equation by differentiation of the dual Langmuir–Freundlich fits of the isotherms at two different temperatures,^{7c,8b} 296 K and 318 K with T -dependent parameters. As shown in Fig. 3, close to zero loading, the Q_{st} for ethylene in MIL-101-Cr-SO₃Ag is 63 kJ mol^{−1}, remarkably higher than that of MIL-101-Cr-SO₃H (10 kJ mol^{−1}). These results highlight the role of introducing Ag(I) ions in further boosting the interactions with ethylene molecules that stem from the formation of the π -complexation bonding between the d orbital of Ag(I) and the π^* orbital of carbon–carbon double bonds in ethylene.¹² In contrast to the high Q_{st} for ethylene, MIL-101-Cr-SO₃Ag shows a significantly lower Q_{st} for ethane with a value of 16 kJ mol^{−1} (Fig. S6, ESI[†]);

Fig. 3 The isosteric heats of adsorption, Q_{st} of C₂H₄ for MIL-101-Cr-SO₃H, and MIL-101-Cr-SO₃Ag.

Fig. 4 IR spectra from ethylene adsorption and desorption on MIL-101-Cr, MIL-101-Cr-SO₃H and MIL-101-Cr-SO₃Ag at room temperature. IR spectrum from gas phase ethylene is also shown for reference.

thus validating that MIL-101-Cr-SO₃Ag featuring the combination of OMS and π -complexation can selectively adsorb ethylene over ethane thereby resulting in high ethylene-ethane adsorption selectivities particularly at a relatively high temperature of 318 K.

In situ IR measurements of ethylene adsorption at room temperature gave further insight into the nature of interactions between ethylene molecules and the Ag(I) ions in MIL-101-Cr-SO₃Ag. As shown in Fig. 4, the appearance of IR features at 975 cm⁻¹ corresponds to the ethylene adsorption on the surface of porous materials. MIL-101-Cr-SO₃Ag exhibits a stronger ethylene interaction than that of MIL-101-Cr and MIL-101-Cr-SO₃H, which is evidenced by the complete disappearance of ethylene IR features at 975 cm⁻¹ for the two compared samples after room temperature desorption in helium purge gas. The extra IR features at 1952 cm⁻¹ (combination mode of -CH₂ wagging), not observed on the MIL-101-Cr and MIL-101-Cr-SO₃H, further confirm stronger ethylene interactions on MIL-101-Cr-SO₃Ag. The blue-shift of the -CH₂ wagging mode can be attributed to the combinative d- π and d- π^* interaction between Ag and ethylene,¹³⁻¹⁶ as a result of the formation of π -complexation between the ethylene and Ag(I) ions in MIL-101-Cr-SO₃Ag.

To further understand the interactions of ethylene-Ag(I) ion and ethylene-Cr(III) OMS, we used electronic structure calculations to estimate the bond length between ethylene and Ag(I) as well as the bond length between ethylene and Cr(III). A (C₆H₃(CO₂)₂)SO₃Ag cluster was considered for this calculation since it is expected that MIL-101-Cr-SO₃Ag contains this moiety. Starting with the sulfonyl terephthalate unit, a silver ion was placed in proximity to the oxygen atoms of the sulfonate group. The Ag(I) ion was optimized to an energetically favorable position within the cluster. Afterwards, an optimized ethylene molecule was placed in proximity to the Ag(I) ion in the (C₆H₃(CO₂)₂)SO₃Ag cluster. The optimization of the C₂H₄-Ag(I) interaction was executed using the DFT method. It was observed that the distances between the Ag(I) ion and the

Fig. 5 The optimized position of an ethylene molecule within (a) (C₆H₃(CO₂)₂)SO₃Ag and (b) [Cr₃O(O₂CH)₆]⁺ clusters.

carbon atoms of the C₂H₄ molecule were found to be 2.18 and 2.19 Å (Fig. 5a). A similar calculation was performed between the ethylene molecule and the Cr(III) OMSs, and the optimized C₂H₄-Cr(III) distances were observed to be 2.54 and 2.55 Å (Fig. 5b). These results suggest that the interactions between ethylene and Ag(I) are much stronger than those between Cr(III) OMSs and they should contribute dominantly to the high adsorption selectivity of MIL-101-Cr-SO₃Ag for ethylene-ethane.

Given the reasonable accuracy of simulated breakthrough characteristics as validated by recent investigations,^{7c,8a,b} we carried out breakthrough simulations for C₂H₄-C₂H₆ mixtures in a fixed bed to demonstrate the feasibility of producing 99.95% + pure C₂H₄ in a Pressure Swing Adsorption (PSA) operation. The simulated breakthrough curves of Fig. S9 (ESI[†]) show transient breakthrough of an equimolar C₂H₄-C₂H₆ mixture in an adsorber bed packed with MIL-101-Cr-SO₃Ag. During the adsorption cycle, C₂H₆ at purities > 99% can be recovered for a certain duration of the adsorption cycle as indicated by the arrow in Fig. S10 (ESI[†]). In addition, ethylene of 99.95% + purity, required as feedstock to the polymerization reactor, can also be recovered during the time interval indicated by the arrow in Fig. S11 (ESI[†]) in the desorption cycle.

In summary, we have demonstrated the introduction of open metal site (OMS) and π -complexation into MOF, affording MIL-101-Cr-SO₃Ag as an efficient adsorbent for separation of ethylene-ethane. MIL-101-Cr-SO₃Ag exhibits significantly higher ethylene-ethane adsorption selectivity at 318 K than benchmark zeolites, MOFs and PAFs reported in the literatures. The high ethylene-ethane adsorption selectivity of MIL-101-Cr-SO₃Ag are mainly attributed to the π -complexation between Ag(I) ions and the double bond of ethylene molecules, which is reflected in the high isosteric heats of adsorption of C₂H₄ and evidenced using *in situ* IR spectroscopy studies and computational calculations. In addition, the possible cooperative contribution from the OMS of Cr(III) to further enhancing the ethylene-ethane adsorption selectivities have been proved by the higher ethylene-ethane adsorption selectivities of MIL-101-Cr-SO₃Ag compared to PAF-1-SO₃Ag. The feasibility of MIL-101-Cr-SO₃Ag for producing 99.95% + pure C₂H₄ in a PSA operation has also been demonstrated by breakthrough simulations. Our strategy of introducing dual functional sites into

MOF to afford high ethylene–ethane adsorption selectivities particularly above room temperature paves a new way for developing MOFs for energy-saving ethylene–ethane and other olefin/paraffin separations.

The authors acknowledge the University of South Florida and the National Science Foundation (DMR-1352065) for financial support of this work. A portion of this research including the *in situ* IR work was conducted at the Center for Nanophase Materials Sciences, which is a DOE Office of Science User Facility. B.S. acknowledges the National Science Foundation (Award No. CHE-1152362), the computational resources that were made available by a XSEDE Grant (No. TG-DMR090028), and the use of the services provided by Research Computing at the University of South Florida.

Notes and references

- 1 R. B. Eldridge, *Ind. Eng. Chem. Res.*, 1993, **32**, 2208.
- 2 S. U. Rege, J. Padin and R. T. Yang, *AIChE J.*, 1998, **44**, 799.
- 3 H. Bux, C. Chmelik, R. Krishna and J. Caro, *J. Membr. Sci.*, 2011, **369**, 284.
- 4 D. J. Safarik and R. B. Eldridge, *Ind. Eng. Chem. Res.*, 1998, **37**, 2571.
- 5 (a) R. T. Yang, *Adsorbents fundamentals and applications*, John Wiley & Sons, Inc., New Jersey, 2003; (b) R. Krishna, *Microporous Mesoporous Mater.*, 2014, **185**, 30; (c) P. Li, Y. He, H. D. Arman, R. Krishna, H. Wang, L. Weng and B. Chen, *Chem. Commun.*, 2014, **50**, 13081; (d) L. Huang and D. Cao, *J. Mater. Chem. A*, 2013, **1**, 9433; (e) M. H. Weston, Y. J. Colón, Y.-S. Bae, S. J. Garibay, R. Q. Snurr, O. K. Farha, J. T. Hupp and S. T. Nguyen, *J. Mater. Chem. A*, 2014, **2**, 299; (f) S. Aguado, G. Bergeret, C. Daniel and D. Farrusseng, *J. Am. Chem. Soc.*, 2012, **134**, 14635; (g) H. Ma, H. Ren, S. Meng, F. Sun and G. Zhu, *Sci. Rep.*, 2013, **3**, 2611; (h) B. Li, Y. Zhang, D. Ma, Z. Shi and S. Ma, *Nat. Commun.*, 2014, **5**, 5537.
- 6 (a) H.-C. Zhou, J. R. Long and O. M. Yaghi, *Chem. Rev.*, 2012, **112**, 673; (b) H.-C. Zhou and S. Kitagawa, *Chem. Soc. Rev.*, 2014, **43**, 5415; (c) W.-Y. Gao, M. Chrzanowski and S. Ma, *Chem. Soc. Rev.*, 2014, **43**, 5841; (d) W.-Y. Gao and S. Ma, *Comments Inorg. Chem.*, 2014, **34**, 125.
- 7 (a) H. Wu, Q. Gong, D. H. Olson and J. Li, *Chem. Rev.*, 2012, **112**, 836; (b) Z. R. Herm, E. D. Bloch and J. R. Long, *Chem. Mater.*, 2014, **26**, 323; (c) Z. Zhang, Z. Z. Yao, S. Xiang and B. Chen, *Energy Environ. Sci.*, 2014, **7**, 2868; (d) C. Y. Lee, Y.-S. Bae, N. C. Jeong, O. K. Farha, A. A. Sarjeant, C. L. Stern, P. Nickias, R. Q. Snurr, J. T. Hupp and S. T. Nguyen, *J. Am. Chem. Soc.*, 2011, **133**, 5228; (e) Y.-S. Bae, C. Y. Lee, K. C. Kim, O. K. Farha, P. Nickias, J. T. Hupp, S. T. Nguyen and R. Q. Snurr, *Angew. Chem., Int. Ed.*, 2012, **51**, 1857; (f) S.-C. Xiang, Z. Zhang, C.-G. Zhao, K. Hong, X. Zhao, D.-R. Ding, M.-H. Xie, C.-D. Wu, M. C. Das, R. Gill, K. Mark Thomas and B. Chen, *Nat. Commun.*, 2011, **2**, 204; (g) K. Li, D. H. Olson, J. Seidel, T. J. Emge, H. Gong, H. Zeng and J. Li, *J. Am. Chem. Soc.*, 2009, **131**, 10368; (h) M. Maes, L. Alaerts, F. Vermoortele, R. Ameloot, S. Couck, V. Finsy, J. F. M. Denayer and D. E. De Vos, *J. Am. Chem. Soc.*, 2010, **132**, 2284; (i) J. W. Yoon, Y.-K. Seo, Y. K. Hwang, J.-S. Chang, H. Leclerc, S. Wuttke, P. Bazin, A. Vimont, M. Daturi, E. Bloch, P. L. Llewellyn, C. Serre, P. Horcajada, J.-M. Grenèche, A. E. Rodrigues and G. Férey, *Angew. Chem., Int. Ed.*, 2010, **49**, 5949; (j) H.-R. Fu, Y. Kang and J. Zhang, *Inorg. Chem.*, 2014, **53**, 4209.
- 8 (a) E. D. Bloch, W. L. Queen, R. Krishna, J. M. Zadrozny, C. M. Brown and J. R. Long, *Science*, 2012, **335**, 1606; (b) Y. He, R. Krishna and B. Chen, *Energy Environ. Sci.*, 2012, **5**, 9107; (c) S. J. Geier, J. A. Mason, E. D. Bloch, W. L. Queen, M. R. Hudson, C. M. Brown and J. R. Long, *Chem. Sci.*, 2013, **4**, 2054; (d) C. Güçüyener, J. van den Bergh, J. Gascon and F. Kapteijn, *J. Am. Chem. Soc.*, 2010, **132**, 17704; (e) U. Böhme, B. Barth, C. Paula, A. Kuhnt, W. Schwieger, A. Mundstock, J. Caro and M. Hartmann, *Langmuir*, 2013, **29**, 8592; (f) Z. Bao, S. Alnemrat, L. Yu, I. Vasiliev, Q. Ren, X. Lu and S. Deng, *Langmuir*, 2011, **27**, 13554; (g) K. Kishida, S. Horike, Y. Watanabe, M. Tahara, Y. Inubushi and S. Kitagawa, *Chem. – Asian J.*, 2014, **9**, 1643; (h) S. Yang, A. J. Ramirez-Cuesta, R. Newby, V. Garcia-Sakai, P. Manuel, S. K. Callear, S. I. Campbell, C. C. Tang and M. Schröder, *Nat. Chem.*, 2014, DOI: 10.1038/NCHEM.2114.
- 9 B. Li, Y. Zhang, R. Krishna, K. Yao, Y. Han, Z. Wu, D. Ma, Z. Shi, T. Pham, B. Space, J. Liu, P. K. Thallapally, J. Liu, M. Chrzanowski and S. Ma, *J. Am. Chem. Soc.*, 2014, **136**, 8654.
- 10 G. Akiyama, R. Matsuda, H. Sato, M. Takata and S. Kitagawa, *Adv. Mater.*, 2011, **23**, 3294.
- 11 A. L. Myers and J. M. Prausnitz, *AIChE J.*, 1965, **11**, 121.
- 12 S. Uchida, R. Kawamoto, H. Tagami, Y. Nakagawa and N. Mizuno, *J. Am. Chem. Soc.*, 2008, **130**, 12370.
- 13 D. Stacchiola, G. Wu, M. Kaltchev and W. T. Tysoe, *Surf. Sci.*, 2001, **486**, 9.
- 14 K. Itoh, T. Kiyohara, H. Shinohara, C. Ohe, Y. Kawamura and H. Nakai, *J. Phys. Chem. B*, 2002, **106**, 10714.
- 15 Y. Huang, *J. Catal.*, 1980, **61**, 461.
- 16 E. L. Uzunova and H. Mikosch, *ACS Catal.*, 2013, 2759.