UvA-DARE (Digital Academic Repository)

Structure and magnetic properties of R(FeVB)₁₂ compounds

Chuang, Y.C.; Zhang, D.; Zhao, T.; Zhang, Z.D.; Liu, P.; Zhao, Z.G.; Sun, W.; de Boer, F.R.

DOI

[10.1016/0925-8388\(94\)01430-2](https://doi.org/10.1016/0925-8388(94)01430-2)

Publication date

1995

Published in

Journal of Alloys and Compounds

[Link to publication](#)

Citation for published version (APA):

Chuang, Y. C., Zhang, D., Zhao, T., Zhang, Z. D., Liu, P., Zhao, Z. G., Sun, W., & de Boer, F. R. (1995). Structure and magnetic properties of R(FeVB)₁₂ compounds. *Journal of Alloys and Compounds*, 221, 60-64. [https://doi.org/10.1016/0925-8388\(94\)01430-2](https://doi.org/10.1016/0925-8388(94)01430-2)

General rights

It is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), other than for strictly personal, individual use, unless the work is under an open content license (like Creative Commons).

Disclaimer/Complaints regulations

If you believe that digital publication of certain material infringes any of your rights or (privacy) interests, please let the Library know, stating your reasons. In case of a legitimate complaint, the Library will make the material inaccessible and/or remove it from the website. Please Ask the Library: <https://uba.uva.nl/en/contact>, or a letter to: Library of the University of Amsterdam, Secretariat, Singel 425, 1012 WP Amsterdam, The Netherlands. You will be contacted as soon as possible.

Structure and magnetic properties of $R(\text{FeVB})_{12}$ compounds

Y.C. Chuang^a, D. Zhang^a, T. Zhao^{a,b}, Z.D. Zhang^a, W. Liu^a, X.G. Zhao^a,
X.K. Sun^a, F.R. de Boer^b

^a Institute of Metal Research, Academia Sinica, 110015 Shenyang, People's Republic of China

^b Van der Waals-Zeeman Laboratory, University of Amsterdam, 1018 XE Amsterdam, Netherlands

Received 6 July 1994

Abstract

Stable $R(\text{FeVB})_{12}$ compounds ($R = \text{Nd, Sm, Y}$) with the ThMn_{12} -type tetragonal structure have been prepared. The Curie temperatures of these compounds are enhanced compared with the boron-free compounds. In some of these compounds the saturation magnetization at 4.2 K is also increased. A spin reorientation is observed at 130 K in $\text{Nd}(\text{FeVB})_{12}$. FOMP transitions occur at 4.2 K in both $\text{Sm}(\text{FeVB})_{12}$ and $\text{Nd}(\text{FeVB})_{12}$ compounds, with onset fields of 11.5 T and 2.2 T, respectively.

Keywords: Magnetic properties; Permanent-magnet applications

1. Introduction

The structure and magnetic properties of ternary compounds of the type $R\text{Fe}_{12-x}\text{M}_x$ ($R = \text{rare earth}$; $M = \text{Ti, V, Cr, Mo, W, etc.}$) have been studied by numerous investigators [1–6]. These compounds crystallize in the tetragonal ThMn_{12} structure in which there is only one crystallographic site for the rare earth and three nonequivalent sites for the M and Fe atoms. High Curie temperatures and high uniaxial anisotropy near room temperature make these systems promising starting materials for permanent-magnet applications [7,8].

The effect of carbon on the structure and magnetic properties of these ThMn_{12} -type rare-earth-transition-metal intermetallics has been investigated recently [9]. Certain carbides of these novel intermetallics were found to exist. Some interesting magnetic phase transitions are observed in these compounds. In the carbide $\text{Nd}(\text{FeMoC})_{12}$ a spin reorientation occurs at 70 K. A first-order magnetization process (FOMP) was observed in $\text{Sm}(\text{FeVC})_{12}$ at 4.2 K. It was found that addition of an appropriate amount of carbon enhances the T–T exchange interaction whereas the R–T exchange interaction is substantially reduced. However, as far as the authors are aware, no work has ever been published concerning the effect of boron addition on the structure and the magnetic properties of these 1:12 compounds. In the present investigation, an attempt has been made to prepare stable isostructural borides of the $R\text{Fe}_{10}\text{V}_2$ compounds with $R = \text{Nd, Sm and Y}$. The magnetic

properties have been studied by a.c. initial susceptibility measurements from 4.2 K to room temperature as well as by high-field magnetization measurements at 4.2 K.

2. Experimental details

Polycrystalline samples with the nominal composition $R\text{Fe}_{10}\text{V}_2\text{B}_{0.5}$ ($R = \text{Nd, Sm and Y}$) were prepared by arc melting. Boron was added in the form of Fe–B alloy containing 20% boron. The as-cast samples were annealed at 950 °C for 3 weeks and checked by X-ray diffraction. The main phase possesses the ThMn_{12} -type tetragonal structure, and the second phase is $\alpha\text{-Fe}$.

X-ray diffraction patterns of random powders and magnetically aligned powders (with incident X-ray beam perpendicular to alignment direction) were used to determine the easy direction of the magnetization at room temperature.

The Curie temperatures were determined by a.c. initial-susceptibility measurements from room temperature up to 600 °C. Spin-reorientation transitions in these compounds at low temperature were studied through a.c. initial-susceptibility measurements from 4.2 K to room temperature.

High-field magnetization measurements up to 35 T were performed at 4.2 K in the High Field Installation at the University of Amsterdam. Powdered samples of cylindrical shape were obtained by aligning the powders at room temperature parallel and perpendicular to the cylinder axis in a magnetic field of 1 T and by fixing

the direction with epoxy resin. The high-field isotherms at 4.2 K were recorded with the external field either parallel or perpendicular to the alignment field. The anisotropy fields B_A were derived from the intersection points of the extrapolated magnetization curves of the parallel and perpendicular aligned materials. Values for the saturation magnetization M_s were derived from the high-field part of the magnetization curves by extrapolation to zero field.

3. Experimental results and discussion

The lattice parameters of these borides are little changed compared with those of the corresponding boron-free compounds. Fig. 1 shows the X-ray diffraction patterns at room temperature of random powders and magnetically aligned powders (X-ray beam perpendicular to the alignment direction) of $\text{NdFe}_{10}\text{V}_2\text{B}_{0.5}$ and $\text{SmFe}_{10}\text{V}_2\text{B}_{0.5}$ alloys, respectively. The X-ray diffraction patterns of random powders of $\text{NdFe}_{10}\text{V}_2\text{B}_{0.5}$ and $\text{SmFe}_{10}\text{V}_2\text{B}_{0.5}$ show reflections of the main phase characteristic of the body-centered tetragonal structure. This is in agreement with the neutron-diffraction result of another alloy, $\text{YFe}_{11}\text{TiB}$, which was prepared in the same way [10]. The neutron diffraction result indicates

Table 1

Curie temperatures of $\text{R}(\text{FeVB})_{12}$ and $\text{RFe}_{10}\text{V}_2$ compounds with $\text{R} = \text{Y}, \text{Nd}, \text{Sm}$

R	Compound	T_c (K)	ΔT_c
Y	$\text{Y}(\text{FeVB})_{12}$	568	34
	$\text{YFe}_{10}\text{V}_2$	534	
Nd	$\text{Nd}(\text{FeVB})_{12}$	607	30
	$\text{NdFe}_{10}\text{V}_2$	577	
Sm	$\text{Sm}(\text{FeVB})_{12}$	632	29
	$\text{SmFe}_{10}\text{V}_2$	603	

that boron atoms prefer to occupy the substitution sites and that the real composition of the main phase is $\text{Y}(\text{FeTiB})_{12}$, suggesting that the main phase obtained in the present work could be identified as $\text{R}(\text{FeVB})_{12}$. Although there is the possibility of the formation of small amounts of the relatively stable V_3B_2 phase, along with the corresponding shift in composition of $\text{REFe}_{10}\text{V}_2\text{B}_{0.5}$ to higher Fe concentrations than $\text{REFe}_{10}\text{V}_2$, we choose to interpret our data, in view of pending neutron diffraction data and the electron probe microanalysis results, as obtained on real B-substituted compounds.

In the patterns of the aligned $\text{NdFe}_{10}\text{V}_2\text{B}_{0.5}$ and $\text{SmFe}_{10}\text{V}_2\text{B}_{0.5}$ powders, only reflections from the (h00) planes are prominent, indicating that the EMD is along the *c*-axis at room temperature. The Curie temperatures of the borides and the virgin compounds have been determined and are listed in Table 1. The observed Curie temperatures of the virgin compounds are comparable with the values reported in literature [1,9]. From Table 1, it can be seen that the Curie temperatures of the $\text{RFe}_{10}\text{V}_2$ compounds are substantially increased by the incorporation of 0.5 boron atom per formula unit.

Results of the high-field magnetization measurements on 4.2 K of the $\text{R}(\text{FeVB})_{12}$ compounds are shown in Figs. 2, 3 and 4. Figs. 2(a) and 2(b) show the high-field magnetization at 4.2 K of $\text{Y}(\text{FeVB})_{12}$ and $\text{YFe}_{10}\text{V}_2$ compounds. In both compounds, the anisotropy field is slightly above 4 T, which is close to the earlier reported value for $\text{YFe}_{10}\text{V}_2$ [1]. The magnetization of $\text{YFe}_{10}\text{V}_2$ at 4.2 K is slightly enhanced by the incorporation of boron.

In $\text{Nd}(\text{FeVB})_{12}$ and $\text{NdFe}_{10}\text{V}_2$ (Figs. 3(a) and 3(b)), the curves for parallel and perpendicular alignment almost coincide, indicating the the magnetocrystalline anisotropy in these compounds is small. FOMP transitions are observed in the high-field magnetization at 4.2 K. Fig. 4(a) shows the field dependence of the magnetization of $\text{Sm}(\text{FeVB})_{12}$ for the field applied parallel and perpendicular to the alignment direction. For comparison, the high-field magnetization of $\text{SmFe}_{10}\text{V}_2$ at 4.2 K is also shown in Fig. 4(b). It is interesting to note that though the Curie temperature

Fig. 1. X-ray diffraction patterns of random and magnetically aligned powders of $\text{Nd}(\text{FeVB})_{12}$ and $\text{Sm}(\text{FeVB})_{12}$. In aligned samples the X-ray beam was directed perpendicular to the alignment direction.

Fig. 2. High-field magnetic isotherms of (a) Y(FeVB)_{12} and (b) $\text{YFe}_{10}\text{V}_2$ compounds at 4.2 K. $\circ$, $M_{\parallel}$; $\bullet$, $M_{\perp}$.

is increased substantially with addition of boron (Table 1), the saturation magnetization appears little improved. In the magnetic isotherms for both Sm(FeVB)_{12} and $\text{SmFe}_{10}\text{V}_2$ at 4.2 K, a slight upward curvature of the magnetization is found for the hard direction, indicating that these compounds exhibit a first-order magnetization process (FOMP). The critical fields for these FOMPs, identified by the peaks in the corresponding dM/dB vs. B curves, are 11.5 T and 11.0 T, respectively.

The magnetic characteristics are summarized in Table 2. The Nd-containing boride has the highest saturation magnetization ($22.9 \mu\text{B/f.u.}$) at 4.2 K. The anisotropy field found for Y(FeVB)_{12} (4.2 T) is comparable with the value reported for $\text{YFe}_{10}\text{V}_2$ in the literature [1].

The temperature dependence of the a.c. initial susceptibility of R(FeVB)_{12} measured from 4.2 K to room temperature is shown in Fig. 5(a). The curve for Nd(FeVB)_{12} exhibits a peak at approximately 130 K indicating the occurrence of a spin reorientation. $\text{NdFe}_{10}\text{V}_2$ undergoes a spin-reorientation transition at 159 K (Fig. 5(b)), which differs from the value ($T_{\text{SR}} = 112$ K) reported by Arnold et al. [3], while the value of

Fig. 3. High-field magnetic isotherms of (a) Nd(FeVB)_{12} and (b) $\text{NdFe}_{10}\text{V}_2$ compounds at 4.2 K. $\circ$, $M_{\parallel}$; $\bullet$, $M_{\perp}$. Insets: dM/dB vs. B curve, B_c indicated by arrow.

Curie temperature agrees well with that reported in Ref. [1].

It is known that in the $\text{RFe}_{12-x}\text{T}_x$ tetragonal structure the crystalline electric field (CEF) at the R site tends to align the R magnetic moment along the c -axis for rare-earth ions such as Sm, Er, Tm or Yb which have a positive second-order Stevens coefficient ($\alpha_2 > 0$), whereas it tends to align the R moment in the basal plane for rare-earth ions with $\alpha_2 < 0$ (e.g. Nd, Tb, Dy etc.). In $\text{RFe}_{10}\text{V}_2$, the Fe-sublattice contribution is represented by $\text{YFe}_{10}\text{V}_2$ in which the EMD is along the c -axis in the temperature range from 4.2 to 300 K. One can infer from this result that in $\text{NdFe}_{10}\text{V}_2$ and Nd(FeVB)_{12} , the Nd and Fe contributions to the magnetocrystalline anisotropy have opposite sign and a competition between them appears. At low temperature, the planar anisotropy of the R ion with $\alpha_2 < 0$ will dominate the uniaxial anisotropy of the Fe sublattice but the R-ion anisotropy rapidly decreases with increasing temperature. At higher temperature, the contribution of the Nd sublattice to the anisotropy will

Fig. 4. High-field magnetic isotherms of (a) $\text{Sm}(\text{FeVB})_{12}$ and (b) $\text{SmFe}_{10}\text{V}_2$ compounds at 4.2 K. $\circ$, $M_{||}$; $\bullet$, $M_{\perp}$. Insets: dM/dB vs. B curve, B_c indicated by arrow.

Table 2
Magnetic characteristics of $\text{R}(\text{FeVB})_{12}$ and $\text{RFe}_{10}\text{V}_2$ at 4.2 K

	M_s ($\mu_B/\text{f.u.}$)	μ_R (μ_B)	μ_{Fe} (μ_B/Fe)	μ_M (μ_B/M)	B_{FOMP} (T)
$\text{Nd}(\text{FeVB})_{12}$	22.9	3.3	1.96	1.64	2.2
$\text{NdFe}_{10}\text{V}_2$	18.5	3.3	1.52	1.26	2.3
$\text{Sm}(\text{FeVB})_{12}$	19.2	0.7	1.85	1.54	11.5
$\text{SmFe}_{10}\text{V}_2$	19.2	0.7	1.85	1.54	11.0
$\text{Y}(\text{FeVB})_{12}$	16.9	0	1.69	1.4	—
$\text{YFe}_{10}\text{V}_2$	15.9	0	1.59	1.3	—

surpass that of the Fe sublattice and consequently a spin reorientation will take place. Arnold et al. [3] found that the spin actually rotates from the basal plane to a cone during this transition. This has been explained by considering higher-order CEF terms. In the case of $\text{Sm}(\text{FeVB})_{12}$ with a Sm ion with $\alpha_j > 0$, the Sm anisotropy will reinforce the axial 3d magnetic anisotropy and consequently no SR transition will occur.

It has been reported that the EMD of $\text{NdFe}_{12-x}\text{M}_x$ ($M = \text{V, Ti and Mo}$) compounds at 4.2 K changes from

Fig. 5. A.c. susceptibilities of (a) $\text{R}(\text{FeVB})_{12}$ ($R = \text{Nd, Sm, Y}$) and (b) $\text{NdFe}_{10}\text{V}_2$ from 4.2 K to room temperature.

basal plane to c -axis upon incorporation of nitrogen because the second-order crystal field coefficient A_{20} has different signs before and after nitrogeneration [11,12]. The results of the present work show that addition of B does not alter the anisotropy of $\text{NdFe}_{10}\text{V}_2$ very much. The decrease of the SR temperature indicates that the planar anisotropy of the Nd sublattice decreases with the B addition.

4. Concluding remarks

In recent years, the search for new permanent-magnet materials has been focussed on the ternary compounds $\text{RFe}_{12-x}\text{M}_x$ ($R = \text{rare earth, M} = \text{Ti, V, Cr, Si, Mo, W}$ etc.) which crystallize in the tetragonal ThMn_{12} structure. The effect of B on the structure and magnetic properties of the $\text{R}(\text{Fe,M})_{12}$ compounds has never been reported. Our present investigation shows that with proper processing such as adequate control of rare-earth losses in the course of preparation, optimizing annealing procedures followed by rapid cooling, stable $\text{R}(\text{Fe,M})_{12}$ boride can be prepared. A number of $\text{R}(\text{FeVB})_{12}$ borides have been prepared with the required ThMn_{12} -type structure. Boron atoms prefer to

occupy substitutional sites in the ThMn_{12} -type compounds.

The Curie temperatures of the $\text{R}(\text{FeVB})_{12}$ ($\text{R} = \text{Nd}, \text{Sm}, \text{Y}$) are substantially enhanced compared with the B-free compounds. The saturation magnetization of $\text{Nd}(\text{FeVB})_{12}$ at 4.2 K is increased. In $\text{Nd}(\text{FeVB})_{12}$ a spin reorientation was observed at 130 K and at 4.2 K a FOMP transition takes place at $B_c = 2.2$ T. A FOMP transition also occurs in $\text{Sm}(\text{FeVB})_{12}$ at 4.2 K with a FOMP onset field at 11.5 T.

Acknowledgements

The present investigation has been carried out within the scientific exchange programme between China and the Netherlands and was supported by the National Natural Science Foundation of China and by the Science and Technology Commission of Shenyang. The assistance of Z.G. Zhao, J.P. Liu, D.C. Zeng, N. Tang and G.F. Zhou is gratefully acknowledged.

References

- [1] F.R. de Boer, Y.K. Huang, D.B. de Mooij and K.H.J. Buschow, *J. Less-Common Met.*, **135** (1987) 199.
- [2] K.H.J. Buschow, D.B. de Mooij, M. Brouha, H.H.A. Smit and R.C. Thiel, *IEEE Trans. Magn.*, **24** (1988) 1611.
- [3] Z. Arnold, P.A. Algarabel and M.R. Ibarra, *J. Appl. Phys.*, **73** (1993) 5905.
- [4] M. Jarczyk and O.D. Chistjakov, *J. Magn. Magn. Mater.*, **82** (1989) 239.
- [5] Q.A. Li, Y. Lu, O. Tegus, R.W. Zhao, J.X. Wu, X.Y. Yin, N. Tang, M.J. Yu, F.M. Yang and F.R. de Boer, *Proc. 2nd Int. Symp. on Physics of Magnetic Materials, Session 2*, 97.
- [6] Yang Hua, Li Qing-an, Tang Ning, Lu Yi, O. Tegus, Yu Ming-jun, F.M. Yang and F.R. de Boer, *Proc. 2nd Int. Symp. on Physics of Magnetic Materials, Session 2, Suppl.* 15.
- [7] P.A. Algarabel and M.R. Ibarra, *Solid State Commun.*, **74** (1990) 231.
- [8] Xie Xu and S.A. Shaheen, *J. Appl. Phys.*, **73** (1993) 6248.
- [9] X.L. Dong, Zhang Zhi-dong, personal communication.
- [10] Zhang Dan, Zhang Zhi-dong, X.K. Sun and Y.C. Chuang, *J. Phys. Cond. Matt.*, accepted for publication.
- [11] Y.Z. Wang and G.C. Hadjipanayis, *J. Appl. Phys.*, **70** (1991) 6009.
- [12] Ying-Chang Yang, Xiao-dong Zhang, Sen-lin Ge, Qi Pan, Lin-shu Kong, Hai-Li Li, Ji-lian Yang, Bai-sheng Zhang, Yong-fan Ding and Chun-tang Ye, *J. Appl. Phys.*, **70** (1991) 6001.